



LOW ALLERGENIC NATURAL RUBBER AND METHOD OF PREPARING LOW  
ALLERGIC ALLERGENIC NATURAL RUBBER—LATEX AND DEPROTEINIZED  
NATURAL RUBBER LATEX, AND  
LOW ALLERGIC NATURAL RUBBER AND DEPROTEINIZED NATURAL RUBBER

5

#### BACKGROUND OF THE INVENTION

The present invention relates to a method of preparing a natural rubber latex and a method of preparing a deproteinized natural rubber latex, which are less likely to  
10 cause allergy, and a low ~~allergie~~ allergenic natural rubber and a deproteinized natural rubber.

Natural rubbers have widely been used in various fields, for example, household appliances such as glove, medical appliances such as surgical glove and various  
15 catheters, lactation appliances, contraceptive device and the like because of features such as large extension, high elasticity and strong film strength. It has recently been reported that, when using medical appliances made of the natural rubber, such as surgical glove and various catheters,  
20 immediate (I type) allergy, which shows symptoms such as respiratory distress and anaphylactoid symptom (e.g. vascular edema, urttication, cyanosis, etc.), is caused. It is presumed that such immediate allergy is caused by a protein, as an antigen, in the natural rubber.

25 Accordingly, a trial of highly removing a protein in a

natural rubber latex has recently been made and Japanese Patent No. 2,905,005 [Japanese Published Unexamined Patent (Kokai Tokkyo Koho Hei) No. 6-56902] discloses a method of adding a proteolytic enzyme such as alkali protease and a surfactant in a natural rubber latex, thereby subjecting to a deproteinization treatment, and sufficiently washing the latex by a centrifugation treatment.

According to the method described in the above patent publication, the protein in the natural rubber can be highly decomposed and removed. Specifically, the amount of the protein contained in the natural rubber, which is represented by the nitrogen content (N%) as determined by the Kjeldahl's method, can be controlled to a very low value such as 0.02% or less. It is generally presumed that the natural rubber is a mixture of a high-molecular component having a number-average molecular weight  $\langle M_n \rangle$  of 1,000,000 to 2,500,000 and a low-molecular component having a number-average molecular weight of 100,000 to 200,000, the former high-molecular component being formed by mutually bonding the low-molecular components via peptide molecules contained in the natural rubber. Assuming that the molecular weight of the low-molecular component, which is deemed to be formed by original biosynthesis, is 100,000 and one peptide molecule in an intermolecular bond, i.e. one nitrogen atom (atomic weight: 14) is bonded based on one rubber molecule of this low-

molecular component, the nitrogen content of the natural rubber is 0.014%. Accordingly, it is considered that about 0.02% of nitrogen is inevitably remained even if subjected to a high deproteinization treatment.

5        In case of subjecting to the deproteinization treatment by the method described in the above publication, an infrared absorption spectrum at ~~3280<sup>-1</sup>—cm~~ 3280cm<sup>-1</sup> peculiar to polypeptide is not observed in a rubber film formed by using the treated natural rubber latex. Therefore, it has been  
10 found that decomposition and removal of the protein are highly achieved by the method described in the above publication.

         However, as is apparent from recent studies, there still exists a possibility of exhibiting allergy even if the  
15 protein is decomposed and removed through various conventionally known deproteinization treatments, including the method described in the above publication.

         According to the present inventors,

         (i) analysis was carried out by an analysis system of a  
20 protein, comprising a combination of a time of flight (TOF) type mass spectrometer and a two-dimensional surface decorative chip so as to confirm what degree a protein and a decomposition product thereof are remained in a natural rubber latex subjected to a deproteinization treatment by a  
25 conventional method, and

(ii) in vitro measurement based on an antigen-antibody reaction using serum of human patients was carried out in place of conventional in vivo measurement by a patch test so as to confirm allergy of a natural rubber latex subjected to a deproteinization treatment by a conventional method.

As a result, it has been found that:

- (I) a protein or protein decomposition product having a number-average molecular weight  $\langle M_n \rangle$  of about 4500 to 4700 is remained and the protein is not sufficiently decomposed, and
- 10 (II) an ~~allergie~~ allergenic protein is included in the amount enough to cause immediate allergy even after the deproteinization treatment.

The term "~~allergie~~ allergenic protein" is defined as follows in the present Invention. Any protein and decomposition product thereof (hereinafter referred to as a "whole protein") in a sample of a natural rubber latex contain the group of an "antigen protein" capable of producing an antibody in human serum. Antibodies produced in human serum are classified into an IgE-antibody capable of causing an allergic reaction and an antibody other than an IgE-antibody capable of causing no allergic reaction. Among the "antigen protein", the antigen protein capable of producing the IgE-antibody, which can cause the allergic reaction, is referred to as an "~~allergie~~ allergenic protein" so as to distinguish from other antigen proteins.

Thus, an object of the present invention is to provide a method of preparing a low ~~allergie~~ allergenic natural rubber latex which substantially contains no ~~allergie~~ allergenic protein and is therefore less likely to cause  
5 allergy.

Another object of the present invention is to provide a method of preparing a deproteinized natural rubber latex which substantially contains no ~~allergie~~ allergenic protein and is therefore less likely to cause allergy.

10 Still another object of the present invention is to provide a natural rubber latex which is less likely to cause allergy because of high degree of the decomposition of a protein.

Further object of the present invention is to provide a  
15 ~~deproteinized~~ deproteinized rubber latex which is less likely to cause allergy because of high degree of the decomposition and removal of a protein.

#### SUMMARY OF THE INVENTION

20 (I) The method of preparing a low ~~allergie~~ allergenic natural rubber latex of the present invention has a feature that it comprises adding a protease having an exopeptidase activity to a natural rubber latex and aging the natural rubber latex, thereby to decompose a protein in the latex to  
25 such a degree that the protein and a protein decomposition

product, which have a number-average molecular weight of 4500 or more, are not detected.

(II) The method of preparing a deproteinized natural rubber latex of the present invention has a feature that it comprises adding an alkali protease to a natural rubber latex, thereby to decompose a protein in the latex, adding a protease having an exopeptidase activity, thereby to further decompose the protein and a decomposition product thereof in the latex, and removing the protein and the decomposition product thereof.

(III) The low ~~allergie~~ allergenic natural rubber of the present invention has a feature that it is a natural rubber obtained by a decomposition treatment of a protein, wherein the protein and a protein decomposition product, which have a number-average molecular weight of 4500 or more, are not detected.

(IV) The deproteinized natural rubber of the present invention has a feature that it is a natural rubber obtained by a decomposition treatment and a removing treatment of a protein, wherein the content of the protein is 0.02% or less in terms of a nitrogen content, an absorption at  $3280\text{ cm}^{-1}$  is not recognized in an infrared absorption spectrum, and the protein and a protein decomposition product, which have a number-average molecular weight of 4500 or more, are not detected.

A protease (proteolytic enzyme) used in a conventional deproteinization treatment is a protease produced mainly by bacteria, and the protease has an optimum pH in an alkali range and also has an endopeptidase activity but does not exhibit an exopeptidase activity. The reason why the alkali protease was mainly used in a conventional deproteinization treatment is as follows: (a) a field latex as a natural rubber is supplied in the form of a so-called ammonia latex prepared by concentrating the latex and adding ammonia for the purpose of preventing coagulation and putrefaction of the latex, and the latex itself exhibits alkalinity; (b) and, therefore, it was necessary to use a so-called alkali protease having an optimum pH in an alkali range so as to avoid coagulation of rubber molecules. Characteristics of a commercially available alkali protease, which has used in a conventional deproteinization treatment, are shown in Table 1.

{Table-1} Table 1

Bacteria which produced enzyme Trade name of enzyme	Activity		pH	Service temperature (°C)
	Endo	Exo		
<i>Bacillus subtilus</i> Biopraser*4	⓪	-	8.1-12	50-70
<i>Bacillus subtilus</i> Proleather FG-F	⓪	-	8.6-12	53-67
<i>Bacillus subtilus</i> PW-102*1	⓪	-	9.0-12	30-50
<i>Bacillus subtilus</i> N "Amano"*3	⓪	-	6.6-8.2	48-62
<i>Bacillus sp</i> Savinase*2	⓪	-	7.7-12	47-58
<i>Bacillus licheniformis</i> Alcalase*2	⓪	-	6.1-11	48-66
<i>Bacillus letus</i> Esperase*2	⓪	-	7.2-10	52-65
<i>Bacillus stearothermo</i> S "Amano"*3	⓪	-	6.6-9.5	62-77

Manufacturer:

1: Kao Corp., 2: Novo-Nordisk Bioindustri A/S, 3: Amano  
5 Enzyme, Inc., 4: Nagase Biochemicals, Ltd.

Activity:

⓪: very high, O: high, -: no activity

Regarding the trade name of bacteria which produced an  
enzyme, the genus is shown in the upper column, while species  
10 are shown in the lower column.

The present inventors have made a trial of performing a  
decomposition treatment of a protein using a protease having  
an exopeptidase activity in place of a conventional alkali  
15 protease. As a result, they have surprisingly found a novel



fact that the protein can be decomposed to such a degree that the protein and the protein decomposition product, which have a number-average molecular weight  $\langle M_n \rangle$  of 4500 or more, do not substantially exist, thereby making it possible to obtain  
5 a natural rubber latex which is less likely to cause allergy. Thus, the invention (I) of the above-described method of preparing a low ~~allergie~~ allergenic natural rubber latex has been completed.

From another point of view, the present inventors have  
10 made a trial of performing a decomposition treatment of a ~~protease~~ protein using a protease having an exopeptidase activity and a removing treatment of the protein and the protein decomposition product thereof, in addition to the decomposition treatment of the protein using a conventional  
15 alkali protease. As a result, they have surprisingly found a novel fact that the protein can be decomposed and removed to such a degree that the protein and the protein decomposition product, which have a number-average molecular weight  $\langle M_n \rangle$  of 4500 or more do not substantially exist, thereby making it  
20 possible to obtain a deproteinized rubber latex which is less likely to cause allergy. Thus, the invention (II) of the above-described method of preparing a low ~~allergie~~ allergenic natural rubber latex has been completed.

In the present invention, the protein and the protein  
25 decomposition product are usually detected by mass

spectrometry, and preferably detected by using an analysis system of a protein, comprising a combination of a time of flight (TOF) type mass spectrometer and a two-dimensional surface decorative chip [for example, protein structure analyzer "Protein Chip™ System", manufactured by Ciphergen Biosystems, Inc.]. According to the Protein Chip™ System, it is made possible to detect a protein in a trace amount such as about 0.1 µg per 1 mL of a natural rubber latex.

Japanese Published Unexamined Patent (Kokai Tokkyo Koho Hei) No. 9-71604 describes that a surfactant is added to a natural rubber latex and, after adjusting the pH by adding a neutralizing agent, a proteolytic enzyme is added, thereby to decompose a protein in the latex. However, the publications merely describes about a decomposition treatment of a protein using an enzyme and does not disclose to what degree a molecular weight of the protein is reduced by such a treatment. The invention described in the publication has a feature in an extraction treatment, which comprises decomposing a protein using an enzyme, incorporating a vulcanizing agent in a latex, forming and vulcanizing the latex, dipping the vulcanized latex in a diluted alkali solution, and extracting the decomposed protein.

In the method of preparing a low ~~allergic~~ allergenic natural rubber latex of the present invention (I), it is preferred to ~~decompose~~ remove the protein and the

decomposition product thereof in the latex after decomposing the protein in view of further reduction of allergy. Such a ~~removing~~ removal treatment is preferably carried out by a centrifugation treatment in view of the removing effect and  
5 the efficiency of the ~~removing~~ removal treatment.

In the method of preparing a deproteinized natural rubber latex of the present invention (II), it is preferred to ~~decompose~~ remove the protein and the decomposition product thereof by a centrifugation treatment in view of the removing  
10 effect and the efficiency of the ~~removing~~ removal treatment.

In the preparation methods of the present inventions (I) and (II), the pH of the latex is preferably adjusted to a neutral range (specifically pH 6 to 9) before treating with a protease having an exopeptidase. The reason is as follows.  
15 That is, since almost any protease having an exopeptidase activity has an optimum pH in the range of 6 to 9, and preferably about 6.5 to 8.5, the effect of the protein decomposition treatment can be enhanced if the pH of the latex is in the neutral range.

20 The protease having an exopeptidase activity used in the present inventions (I) and (II) is preferably a protease produced by microorganisms, which belong to the genus ~~Aspergillus~~ Aspergillus or ~~Rhizopus~~ Rhizopus, as a kind of filamentous bacteria. The peptidase derived from filamentous  
25 bacteria is suited for ~~realization~~—of high degree

decomposition of the protein.

The protease having an exopeptidase activity is more preferably a protease produced by microorganisms, which belong to *Aspergillus oryzae*, microorganisms which belong to *Aspergillus mellus*, or a protease produced by microorganisms which belong to *Rhizopus oryzae*, among those produced by microorganisms which belong to the genera described above.

In the preparation methods of the present inventions (I) and (II), the decomposition treatment of the protein is preferably carried out in the presence of a surfactant from such a view point that rubber molecules are stably dispersed in the latex, thereby to improve the ~~effect of decomposing~~ decomposition of the protein.

Regarding the low ~~allergie~~ allergenic natural rubber of the present invention (III), as is apparent from the fact that the protein and the protein decomposition product, which have a number-average molecular weight  $\langle M_n \rangle$  of 4500 or more, are not detected, the protein is highly decomposed as compared with the case when subjected to a deproteinization treatment by a conventionally known method. Therefore, it is considered that almost any portion, which can serve as an antigen capable of an IgE-antibody against human serum, is eliminated or denatured by the decomposition treatment, and allergy is less likely to ~~be caused~~ occur.

Regarding the low ~~allergie~~ allergenic natural rubber of

the present invention (III), since the protein is ~~decomposed~~  
~~extremely highly~~ highly decomposes, a possibility of causing  
allergy is markedly reduced. Accordingly, it is suited for  
use as raw materials of household appliances such as ~~glove~~  
5 gloves, medical appliances such as a surgical catheter,  
lactation appliances, contraceptive device and the like.

Regarding the deproteinized natural rubber of the  
present invention (IV), it is apparent that the total amount  
of the protein contained in the natural rubber is highly  
10 reduced similar to a conventional deproteinization treatment  
because the content of the protein is 0.02% or less in terms  
of a nitrogen content and an absorption at  $3280\text{ cm}^{-1}$  is not  
recognized in an infrared absorption spectrum.

Moreover, as is apparent from the fact that the protein  
15 and the protein decomposition product, which have a number-  
average molecular weight  $\langle M_n \rangle$  of 4500 or more, are not  
detected, the protein is highly decomposed as compared with  
the natural rubber subjected to a deproteinization treatment  
by a conventionally known method. Therefore, it is  
20 considered that almost any portion, which can serve as an  
antigen capable of an IgE-antibody against human serum, is  
eliminated or denatured by the decomposition treatment, and  
~~allergy~~ an allergic reaction is less likely to ~~be caused~~  
occur.

25 Regarding the deproteinized natural rubber of the

present invention (IV), since the protein is ~~is decomposed~~  
extremely highly decomposes, a possibility of causing allergy  
is markedly reduced. Accordingly, it is suited for use as  
raw materials of household appliances such as glove, medical  
5 appliances such as a surgical catheter, lactation appliances,  
contraceptive device and the like.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a graph showing the measurement results of a  
10 number-average molecular weight  $\langle M_n \rangle$  of the remained protein  
and protein decomposition product with respect to low  
allergie allergenic natural rubber latexes obtained in  
Examples 1 and 13, which have been subjected only to a  
protein decomposition treatment.

15 Fig. 2 is a graph showing the measurement results of a  
number-average molecular weight  $\langle M_n \rangle$  of the remained protein  
and protein decomposition product with respect to low  
allergie allergenic natural rubber latexes obtained in  
Examples 1 and 13, which have been subjected to a protein  
20 decomposition treatment and a protein removing treatment.

Fig. 3 is a graph showing the measurement results of a  
number-average molecular weight  $\langle M_n \rangle$  of the remained protein  
and protein decomposition product with respect to  
deproteinized natural rubber latexes obtained in Comparative  
25 Examples 1 and 3, and Comparative Examples 2 and 4 which have

been subjected to a protein decomposition treatment and a protein removing treatment.

Fig. 4 is a graph showing the measurement results of a number-average molecular weight  $\langle M_n \rangle$  ~~wit~~ with respect to the protein ~~remained~~ remaining in a high ammonia-treated latex.

Fig. 5 is a graph showing the measurement results of a number-average molecular weight  $\langle M_n \rangle$  of the ~~remained~~ remaining protein and protein decomposition product with respect to deproteinized natural rubber latexes obtained in Examples 7 and 19.

Fig. 6 is a graph showing the measurement results of a number-average molecular weight  $\langle M_n \rangle$  of the ~~remained~~ remaining protein and protein decomposition product with respect to deproteinized natural rubber latexes obtained in Examples 9 and 21.

Fig. 7 is a graph showing the measurement results of a number-average molecular weight  $\langle M_n \rangle$  of the ~~remained~~ remaining protein and protein decomposition product with respect to deproteinized natural rubber latexes obtained in Examples 8 and 22.

Fig. 8 is a graph showing the measurement results of a number-average molecular weight  $\langle M_n \rangle$  of the ~~remained~~ remaining protein and protein decomposition product with respect to deproteinized natural rubber latexes obtained in Examples 10 and 23.

## DETAILED DESCRIPTION OF THE INVENTION

A. The method of preparing a low ~~allergie~~ allergenic natural rubber latex of the present invention (I) will be  
5 described in detail.

The method of preparing a low ~~allergie~~ allergenic natural rubber latex of the present invention (I) has a feature, as described above, that (1) it comprises adding a protease having an exopeptidase activity to a natural rubber  
10 latex and aging the natural rubber latex, thereby to decompose a protein in the latex to such a degree that the protein and a protein decomposition product, which have a number-average molecular weight of 4500 or more, are not detected. The present invention includes the following  
15 embodiments.

(2) The method of preparing a low ~~allergie~~ allergenic natural rubber latex described in the term (1), wherein the protein and the decomposition product thereof in the latex are removed after decomposing the protein.

20 (3) The method of preparing a low ~~allergie~~ allergenic natural rubber latex described in the term (2), wherein the protein and the decomposition product thereof are removed by a centrifugation treatment.

(4) The method of preparing a low ~~allergie~~ allergenic  
25 natural rubber latex described in the term (1), wherein the



pH of the latex is adjusted to a neutral range before treating with the protease having an exopeptidase activity.

(5) The method of preparing a low ~~allergie~~ allergenic natural rubber latex described in the term (1), wherein the  
5 protease having an exopeptidase activity is produced by microorganisms which belongs to the genus ~~Aspergillus~~ Aspergillus or ~~Rhizopus~~ Rhizopus.

(6) The method of preparing a low ~~allergie~~ allergenic natural rubber latex described in the term (5), wherein the  
10 microorganisms which belong to the genus ~~Aspergillus~~ Aspergillus are microorganisms which belong to Aspergillus oryzae.

(7) The method of preparing a low ~~allergie~~ allergenic natural rubber latex described in the term (5), wherein the  
15 microorganisms which belong to the genus ~~Aspergillus~~ Aspergillus are microorganisms which belong to Aspergillus mellus.

(8) The method of preparing a low ~~allergie~~ allergenic natural rubber latex described in the term (5), wherein the  
20 microorganisms which belong to the genus ~~Rhizopus~~ Rhizopus are microorganisms which belong to Rhizopus oryzae.

(9) The method of preparing a low ~~allergie~~ allergenic natural rubber latex described in the term (1), wherein the decomposition treatment of the protein is carried out in the  
25 presence of a surfactant.

The respective constituent features of the present invention will now be described.

[Protease having an exopeptidase activity]

The enzyme for decomposing the protein used in the present invention is a protease having an exopeptidase activity.

In the present invention, the effect of reducing the molecular weight of the protein and the decomposition effect can be further enhanced by the decomposition using an endopeptidase, along with the decomposition using an exopeptidase. It is preferred to use a protease having both an exopeptidase activity and an endopeptidase activity in the preparation method of the present invention.

In case the protease having an exopeptidase activity is limited from its origin, the protease is preferably a protease produced by microorganisms, which belong to the genus ~~Aspergillus~~ Aspergillus or ~~Rhizopus~~ Rhizopus, as a kind of filamentous bacteria.

Examples of the microorganisms which belong to the ~~Aspergillus~~ Aspergillus include *Aspergillus oryzae*, *Aspergillus mellus*, *Aspergillus niger*, *Aspergillus awamori*, *Aspergillus glaucus*, *Aspergillus flavus*, *Aspergillus sojae* and the like.

Examples of the microorganisms which belong to the ~~Rhizopus~~ Rhizopus include *Rhizopus oryzae*, *Rhizopus*

*javanicus*, *Rhizopus delemar*, *Rhizopus nigricans* and the like.

The protease having an exopeptidase activity used in the present invention is preferably a protease produced by microorganisms, which belong to *Aspergillus oryzae*, microorganisms, which belong to *Aspergillus mellus*, or a protease produced by microorganisms which belong to *Rhizopus oryzae*, among those described above.

Characteristics of a commercially available protease having an exopeptidase activity are shown in Table 2.

{Table 2} Table 2

Filamentous bacteria which produced enzyme Trade name of enzyme	Activity		pH	Service temperature (°C)
	Endo	Exo		
<i>Aspergillus oryzae</i> A "Amano" G*3	○	○	5.4-10	46-58
<i>Aspergillus oryzae</i> M "Amano"*3	○	⊙	3.0-6.2	35-62
<i>Aspergillus oryzae</i> Umamizyme*3	○	⊙	6.2-8.2	30-60
<i>Aspergillus oryzae</i> Flavorzyme*2	○	○	4.5-7.7	38-58
<i>Aspergillus mellus</i> P "Amano" 3G*3	○	○	6.0-9.2	37-49
<i>Aspergillus oryzae</i> Peptidase R*3	○	⊙	6.2-7.4	30-50

Manufacturer:

1: Kao Corp., 2: Novo-Nordisk Bioindustri A/S, 3: Amano Enzyme, Inc., 4: Nagase Biochemicals, Ltd.

Activity:

⊙: very high, ○: high, -: no activity

Regarding the trade name of bacteria which produced an

enzyme, the genus is shown in the upper column, while species are shown in the lower column.

(Raw latex)

5       The natural rubber latex, which is a starting material to obtain the low ~~allergie~~ allergenic natural rubber latex of the present invention, means a latex collected from rubber trees and a flesh ~~filed~~ field latex and a commercially available ammonia-treated latex can be used as the latex.

10       [Method of protein decomposition treatment]

[Decomposition treatment of protein]

In the preparation method of the present invention, the decomposition treatment of the protein by a protease having an exopeptidase activity is carried out by adding the  
15       protease or a mixture of two or more proteases in a natural rubber latex, and aging the latex for about several hours to one week.

The amount of the protease having an exopeptidase activity is set according to the peptidase activity and is  
20       not specifically limited, but may be usually set within a range from about 0.001 to 10% by weight based on the rubber solid content of the field latex or ammonia-treated latex. When the amount of the protease is smaller than 0.001% by weight, there is a possibility that the sufficient effect of  
25       decomposing the protein is not obtained. On the other hand,

when the amount exceeds 10% by weight, the cost increases because of excess enzyme and the enzymatic activity is likely to be reduced.

The peptidase activity of the protease having an  
5 exopeptidase activity used in the present invention is not specifically limited, but is preferably 30  $\mu$ /g or more (LGG method).

The pH of the latex in the protein decomposition treatment by the protease is set according to an optimum pH  
10 of the protease to be used. Since almost any protease having an exopeptidase activity is a so-called neutral protease having an optimum pH in a neutral range, specifically within a range from 6 to 9, and preferably from 6.5 to 8.5, the pH of the latex to be treated with the protease is preferably  
15 adjusted within a neutral range, specifically within a range from 6 to 9, and preferably from 6.5 to 8.5. To adjust the pH of the latex to a neutral range, sodium dihydrogenphosphate, formalin, diluted hydrochloric acid or the like may be added to the latex.

20 The temperature of the latex in the protein decomposition treatment by the protease is set according to the optimum temperature of the protease to be used and is not specifically limited, but is preferably set within a range from 5 to 90°C, and more preferably from 20 to 60°C.

The surfactant as a stabilizer may be previously added before the protein decomposition treatment by the protease or added in the amount within a range from 0.01 to 10% by weight during the treatment by the protease.

(Removing treatment of protein and protein decomposition product)

After the completion of the protein decomposition treatment, the natural rubber latex may be further subjected to treatments such as centrifugation, coagulation of the rubber component, ultrafiltration and the like. The protein and the decomposition product thereof can be separated from the rubber component and removed by these treatments. By subjecting to such a removing treatment, a natural rubber latex having a lower allergy can be provided.

In case the removing treatment of the protein and the decomposition product thereof is carried out by centrifugation, the protein and the decomposition product thereof are sufficiently removed by only one centrifugation treatment, but the centrifugation treatment may be carried out twice or more times as far as an adverse influence is exerted by loss of the rubber component and reduction in yield.

[Surfactant]

In case the decomposition treatment of the protein is

carried out to prepare a low ~~allergie~~ allergenic natural rubber of the present invention, a surfactant as a stabilizer is preferably added to the latex before subjecting to a treatment by the protease having an exopeptidase activity or  
5 during the treatment. In case the pH of the ammonia-treated latex is adjusted to a neutral range or the decomposition treatment of the protein is carried out, the addition of the surfactant is desired to prevent coagulation of the rubber component.

10        Examples of the surfactant include, but are not limited to, various anionic surfactants, nonionic surfactants and cationic surfactants which have conventionally been known. Since almost any protease having an exopeptidase activity has an optimum pH in a neutral range, preferred are those which  
15 exhibit stable surface activity in a neutral range, and preferably pH 6.5 to 8.5.

Surfactants, which can be used in the present invention, are shown below. The following surfactants can be used alone or in combination.

20        (Anionic surfactant)

Examples of the anionic surfactant include carboxylate, sulfonate, sulfate and phosphate surfactants.

Examples of the carboxylate anionic surfactant include fatty acid salt, polyhydric carboxylic acid salt, rosin acid  
25 salt, dimer acid salt, polymer acid salt and tall oil fatty

acid salt, which have 6 to 30 carbon atoms. Among these, carboxylic acid salt having 10 to 20 carbon atoms is preferred. When the number of carbon atoms is smaller than 6, the action for dispersion and emulsification of the protein and impurities is likely to be insufficient. On the other hand, when the number of carbon atoms exceeds 30, it is likely to be difficult to disperse in water.

Examples of the sulfonate anionic surfactant include alkylbenzenesulfonic acid salt, alkyl-naphthalenesulfonic acid salt, naphthalenesulfonic acid salt and diphenyl ether sulfonic acid salt.

Examples of the sulfate surfactant include alkylsulfuric ester salt, polyoxyalkylene alkylsulfuric ester salt, polyoxyalkylene alkyl phenyl ether sulfuric acid salt, tristyrenated phenol sulfuric ester salt and polyoxyalkylene distyrenated phenol sulfuric ester salt.

Examples of the phosphate anionic surfactant include alkylphosphoric acid ester salt and polyoxyalkylenephosphoric acid ester salt.

Examples of the salt of these compounds include metal salts (for example, Na, K, Ca, Mg and Zn salts), ammonia salt and amine salt (for example, triethanolamine salt).

(Nonionic surfactant)

Examples of the nonionic surfactant include polyoxyalkylene ether, ~~polyoxyalkylene~~ polyoxyalkylene



ester, polyhydric alcohol fatty acid ester, saccharide fatty acid ester and alkyl polyglycoside nonionic surfactants.

Examples of the polyoxyalkylene ether nonionic surfactant include polyoxyalkylene alkyl ether, 5 polyoxyalkylene alkyl phenyl ether, polyoxyalkylene polyol alkyl ether, polyoxyalkylene styrenated phenol ether, polyoxyalkylene distyrenated phenol ether and polyoxyalkylene tristyrenated phenol ether. Examples of the polyol include polyhydric alcohol having 2 to 12 carbon atoms, for example, 10 propylene glycol, glycerin, sorbitol, sucrose, pentaerythritol and sorbitan.

Examples of the polyoxyalkylene ester nonionic surfactant include polyoxyalkylene fatty acid ester.

Examples of the polyhydric alcohol fatty acid ester 15 nonionic surfactant include fatty acid ester of polyhydric alcohol having 2 to 12 carbon atoms or fatty acid ester of polyoxyalkylene polyhydric alcohol. Specific examples thereof include sorbitol fatty acid ester, sorbitan fatty acid ester, fatty acid monoglyceride, fatty acid diglyceride 20 and polyglycerin fatty acid ester. Polyalkylene oxide adducts of these surfactants (for example, polyoxyalkylene sorbitan fatty acid ester, polyoxyalkylene glycerin fatty acid ester, etc.) can also be used.

Examples of the saccharide fatty acid ester nonionic 25 surfactant include fatty acid esters of sucrose, glucose,

maltose, fructose and polysaccharides, and polyalkylene oxide adducts of these surfactants can also be used.

Examples of the alkyl polyglycoside nonionic surfactant include alkyl glucoside, alkyl polyglucoside, polyoxyalkylene  
 5 alkyl glucoside and polyoxyalkylene ~~alkyl polyglucoside~~,  
alkyl polyglucoside and fatty acid esters. Polyalkylene oxide adducts of these surfactants can also be used.

Examples of the alkyl group in these nonionic surfactants include alkyl group having 4 to 30 carbon atoms.  
 10 Examples of the polyoxyalkylene group include those having a  $C_{2-4}$  alkylene group, for example, those in which the addition mol number of ethylene oxide is from about 1 to 50 mols. Examples of the fatty acid include straight-chain or branched saturated or unsaturated fatty acid having 4 to 30 carbon  
 15 atoms.

(Cationic surfactant)

Examples of the cationic surfactant include alkylamine salt, alkylamine derivative and quaternized compound thereof, and imidazolinium salt cationic surfactants.

20 Examples of the alkylamine salt cationic surfactant include salts of primary amine, secondary amine and tertiary amine.

The alkylamine derivative cationic ~~surfaetnat~~  
surfactant has at least one of an ester group, an ether group  
 25 and an amide group in a molecule and examples thereof include

polyoxyalkylene (AO) alkylamine and a salt thereof, alkyl ester amine (including AO adduct) and a salt thereof, alkyl ether amine (including AO adduct) and a salt thereof, alkylamideamine (including AO adduct) and a salt thereof, 5 alkyl ester amideamine (including AO adduct) and a salt thereof, and alkyl ether amideamine (including AO adduct) and a salt thereof.

Examples of the salt include hydrochloride, phosphate, acetate, alkylsulfonic acid ester, alkylbenzenesulfonic acid, 10 alkyl-naphthalenesulfonic acid, fatty acid, organic acid, alkylphosphoric acid ester, alkyl ether carboxylic acid, alkylamide ether carboxylic acid, anionic oligomer and anionic polymer. Specific examples of the acetate among the alkylamine derivative cationic surfactant include 15 coconutamine acetate and stearylamine acetate. The alkyl group in the alkylamine salt and alkylamine derivative cationic surfactants usually includes, but is not limited to, straight-chain, branched or Guerbet-shaped alkyl groups having 8 to 22 carbon atoms.

20 Examples of the quaternized compound of the alkylamine salt and alkylamine derivative cationic surfactants include those prepared by quaternizing the alkylamine salt and alkylamine derivative with methyl chloride, methyl bromide, dimethylsulfuric acid or diethylsulfuric acid. Specific 25 examples thereof include alkyltrimethylammonium halide such

as lauryltrimethylammonium halide, cetyltrimethylammonium halide, or stearyltrimethylammonium halide; dialkyldimethylammonium halide such as distearyldimethylammonium halide; trialkylmethylammonium halide; dialkylbenzylmethylammonium halide; or alkylbenzyldimethylammonium halide.

Examples of the imidazolinium salt cationic surfactant include 2-heptadecenyl-hydroxyethylimidazoline.

Examples of those which exhibit stable surface activity at the pH within a range from 6.5 to 8.5 among the surfactants described above include polyoxyethylene nonyl phenyl ether as the nonionic surfactant and sodium polyoxyethylene alkyl phenyl ether sulfate as the anionic surfactant.

(Other additives)

In the method of preparing the low ~~allergie~~ allergenic natural rubber latex of the present invention, other additives may be used optionally, in addition to the respective components described above.

These other additives include pH adjustors, for example, phosphate such as monopotassium phosphate, dipotassium phosphate or sodium phosphate; acetate such as potassium acetate or sodium acetate; acids such as sulfuric acid, acetic acid, hydrochloric acid, citric acid and succinic acid, or salts thereof; and ammonia, sodium

hydroxide, potassium hydroxide, sodium carbonate, and sodium hydrogencarbonate. Examples thereof include enzymes such as lipase, esterase, amylase, laccase and cellulase. Examples thereof include dispersants such as styrenesulfonic acid copolymer, formalin naphthalenesulfonate condensate, ligninsulfonic acid, polycyclic aromatic sulfonic acid copolymer, homopolymer/copolymer of acrylic acid and maleic anhydride, isobutylene-acrylic acid, and isobutylene-maleic anhydride copolymer.

10 [Degree of protein decomposition treatment and allergy]

In the low ~~allergie~~ allergenic natural rubber latex subjected to the protein decomposition treatment by the protease having an exopeptidase activity according to the preparation method of the present invention, the protein is  
15 remained in the same amount as that of the natural rubber latex as control in case of comparing by the nitrogen content (N%) by the Kjeldahl's method.

However, the low ~~allergie~~ allergenic natural rubber latex obtained by the method of the present invention has a  
20 very small content of the protein having a large molecular weight and the ~~allergie~~ allergenic protein as compared with the deproteinized natural rubber latex subjected to the deproteinization treatment by a conventional method. Specifically, the protein and the protein decomposition  
25 product, which have a number-average molecular weight  $\langle M_n \rangle$  of

4500 or more, are not detected from the low ~~allergie~~  
allergenic natural rubber latex obtained by the method of the  
present invention.

As is apparent from Comparative Examples described  
5 hereinafter, the protein and the protein decomposition  
product, which have a number-average molecular weight  $\langle M_n \rangle$  of  
4500 or more, are detected from the deproteinized natural  
rubber latex (rubber solid content: ~~about 30%~~ about 30%)  
subjected to the deproteinization treatment by a conventional  
10 method (one enzyme treatment and one centrifugation  
treatment). On the other hand, as is apparent from Examples  
described hereinafter, the protein and the protein  
decomposition product, which have a number-average molecular  
weight  $\langle M_n \rangle$  of 4500 or more, are not detected from the  
15 natural rubber latex subjected to the protein decomposition  
treatment by the method of the present invention (one enzyme  
treatment and no centrifugation treatment).

As described above, the degree that the protein and the  
protein decomposition product, which have a number-average  
20 molecular weight  $\langle M_n \rangle$  of 4500 or more, are not detected means  
that the protein is decomposed to such a degree that allergy  
caused by the protein does not substantially occur.  
Regarding the low ~~allergie~~ allergenic natural rubber latex of  
the present invention, although the total amount of the  
25 protein remained in the latex is large, a possibility of

causing immediate allergy due to the protein is markedly reduced.

In the case the protein was subjected to the  
5 decomposition treatment by the preparation method of the  
present invention, as described above, the protein and the  
protein decomposition product, which have a number-average  
molecular weight of 4500 or more, are not detected.  
According to more preferred conditions of the present  
10 invention, the protein can be decomposed to such a degree  
that the protein and the protein decomposition product, which  
have a number-average molecular weight of 2000 or more, more  
preferably 1500 or more, are not detected.

In the case the protein was subjected to the  
15 decomposition treatment by the preparation method of the  
present invention, the content index of the ~~allergie~~  
allergenic protein measured by the RAST-inhibition method can  
be reduced to 10  $\mu\text{g/g}$  or less, preferably 5  $\mu\text{g/g}$  or less, and  
more preferably 2  $\mu\text{g/g}$  or less.

20 It is generally considered that allergy caused by the  
protein is less likely to occur, substantially, when the  
content index of the ~~allergie~~ allergenic protein is smaller  
than 10  $\mu\text{g/g}$  or less.

As used herein, the term "content index of an ~~allergie~~  
25 allergenic protein" is an index in which the degree of the

content of a protein capable of producing an IgE-antibody against human serum (capable of serving as an antigen) is indicated based on a general high ammonia latex (HA latex), and is a value which relatively indicates the degree of allergy.

Although the total amount of the protein in the natural rubber latex and the total amount of the dissolved protein can be determined by analysis, the amount of the ~~allergie~~ allergenic protein and that of ~~non-allergie~~ non-allergenic protein can not be determined separately. Therefore, allergy of the natural rubber latex is evaluated as a relative value of allergy based on a conventional natural rubber latex, for example, a HA latex herein.

The "content index of an ~~allergie~~ allergenic protein" is calculated by a Competitive RAST-immunoinhibition method [see X. Baur et al., Allergy, 52, 661-664 (1997)] using a Pharmacia Cap system and is specifically calculated in the following procedure.

First, an extract of a HA latex (non-ammonia natural rubber latex in the above literature) as a standard ~~allergie~~ allergenic sample is aged by mixing with an IgE-antibody in human serum, thereby enabling the antigen-antibody reaction between the ~~allergie~~ allergenic protein in the HA latex and the IgE-antibody to proceed. As a supply source of the IgE-antibody, serum of persons suffering from latex allergy is



used. The IgE-antibody remained without causing the antigen-antibody reaction is reacted with an Immuno-Cap latex antigen of a solid phase and the immobilized IgE-antibody is bonded with an antibody labeled with an enzyme ( $\beta$ -D-galactosidase),  
5 and then the amount of the remained IgE-antibody is determined by measuring the fluorescence intensity. The degree of allergy for the dissolved protein of the HA latex is determined by this measured value. Using several kinds of samples having different dilution degrees of the HA latex,  
10 the degree of allergy is measured and a calibration curve is made. Also with respect to the natural rubber latex as a measuring sample, the degree of allergy is determined in the same manner as described above. As a result, if the resulting degree of allergy is the same as that obtained when  
15 the total amount of the dissolved protein of the HA latex is 10  $\mu$ g per 1 g of the rubber, the content index of the ~~allergic~~ allergenic protein of the measuring sample is 10  $\mu$ g/g.

B. The method (II) of preparing a deproteinized natural  
20 rubber latex of the present invention will be described.

The method of preparing a deproteinized natural rubber latex of the present invention has a feature, as described above, that (10) it comprises adding an alkali protease to a natural rubber latex, thereby to decompose a protein in the  
25 latex, adding a protease having an exopeptidase activity,

thereby to further decompose the protein and a decomposition product thereof in the latex, and removing the protein and the decomposition product thereof. The present invention includes the following embodiments.

5           (11) The method of preparing a deproteinized natural rubber latex described in the term (10), wherein the protein and the decomposition product thereof are removed by a centrifugation treatment.

          (12) The method of preparing a deproteinized natural  
10 rubber latex described in the term (10), wherein the pH of the latex is adjusted to a neutral range before treating with the protease having an exopeptidase activity.

          (13) The method of preparing a deproteinized natural rubber latex described in the term (10), wherein the protease  
15 having an exopeptidase activity is produced by microorganisms which belong to the genus ~~Aspergillus~~ Aspergillus or ~~Rhizopus~~ Rhizopus.

          (14) The method of preparing a deproteinized natural rubber latex described in the term (13), wherein the  
20 microorganisms which belong to the genus ~~Aspergillus~~ Aspergillus are microorganisms which belong to *Aspergillus oryzae*.

          (15) The method of preparing a deproteinized natural rubber latex described in the term (13), wherein the  
25 microorganisms which belong to the genus *Aspergillus* are

microorganisms which belong to *Aspergillus mellus*.

(16) The method of preparing a low—~~allergic~~  
~~deproteinized~~ natural rubber latex described in the term  
 (13), wherein the microorganisms which belong to the genus  
 5 ~~Rhizopus~~ Rhizopus are microorganisms which belong to *Rhizopus*  
*oryzae*.

(17) The method of preparing a deproteinized natural  
 rubber latex described in the term (10), wherein the  
 decomposition treatment of the protein is carried out in the  
 10 presence of a surfactant.

The respective constituent features of the present  
 invention will now be described.

[Protease]

The enzyme for decomposing a protein, which is used to  
 15 prepare a deproteinized natural rubber of the present  
 invention, includes two kinds of enzymes, such as  
 conventionally known protease (alkali protease) and protease  
 having an exopeptidase activity.

(Conventionally known protease)

20 The conventionally known protease is not specifically  
 limited, and may be either a protease derived from  
 filamentous bacteria or a protease derived from yeast. Among  
 these proteases, a protease derived from bacteria is  
 preferably used. In general, the protease derived from  
 25 bacteria is a protease, which has an optimum pH in an alkali

range and only has an endoprotease activity.

Specific examples of the protease derived from bacteria include proteases described in Table 1.

(Protease having exopeptidase activity)

5       The protease having an exopeptidase activity may also have an endopeptidase activity. In this case, the effect of reducing the molecular weight of the protein and the efficiency of the decomposition can be further improved.

10       As the protease having an exopeptidase activity, the same one described in the preparation method (I) of the present invention can be used.

[Raw latex]

15       As the natural rubber latex as a starting material for obtaining the deproteinized natural rubber latex of the present invention, the same one described in the preparation method (I) of the present invention can be used.

[Method of preparing deproteinized natural rubber latex]

20       The method of preparing a deproteinized natural rubber latex of the present invention has a feature, as described above, that it comprises the steps of:

(1) performing a decomposition treatment of a protein using a conventionally known protease (alkali protease), and

25       (2) optionally adjusting the pH of a latex and performing a decomposition treatment of a protein using a protease having

an ~~exopeptidase~~ exopeptidase activity, and then removing the protein and the decomposition product thereof from the latex thus obtained.

(Decomposition treatment of protein by alkali protease)

5        In the method of preparing a deproteinized natural rubber of the present invention, the decomposition treatment of the protein by the conventionally known alkali protease, as the step (1), is carried out by adding the alkali protease or a mixture of two or more proteases in a natural rubber  
10 latex, and aging the latex for about several hours to one week.

      The amount of the alkali protease is set according to the activity of the protease to be used and is not specifically limited, but may be usually set within a range  
15 from about 0.001 to 10% by weight based on the field latex or ammonia-treated latex. When the amount of the alkali protease is smaller than 0.001% by weight, there is a possibility that the sufficient effect of decomposing the protein is not obtained. On the other hand, when the amount  
20 exceeds 10% by weight, the cost increases because of excess enzyme and the enzymatic activity is likely to be reduced.

      The activity of the alkali protease used in the present invention is not specifically limited.

      The pH of the latex in the protein decomposition  
25 treatment by the alkali protease may be appropriately set

according to an optimum pH of the protease to be used.

The temperature of the latex in the protein decomposition treatment by the alkali protease is set according to the optimum temperature of the protease to be  
5 used and is not specifically limited, but is preferably set within a range from 5 to 90°C, and more preferably from 20 to 60°C.

The surfactant as a stabilizer may be previously added before the protein decomposition treatment by the alkali  
10 protease or added in the amount within a range from 0.01 to 10% by weight during the treatment by the protease.

(Decomposition treatment of protein by exopeptidase)

The decomposition treatment of the protein by the protease having an exopeptidase activity, as the step (2), is  
15 carried out by adding the protease having an exopeptidase activity or a mixture of two or more proteases in a natural rubber latex, and aging the latex for about several hours to one week. This decomposition treatment can be carried out in the same manner as in the preparation method (I) of the  
20 present invention.

(Removing treatment of protein and protein decomposition product)

After the completion of the protein decomposition treatment, the natural rubber latex may be further subjected  
25 to treatments such as centrifugation, coagulation of the

rubber component, ultrafiltration and the like. The protein and the decomposition product thereof can be separated from the rubber component and removed by these treatments. By subjecting to such a removing treatment, a deproteinized  
5 natural rubber latex having very low allergy can be provided.

Although the removing treatment may be carried out after the decomposition treatment of the protein by the alkali protease, as the step (1), and after the decomposition treatment of the protein by the protease having an  
10 exopeptidase activity, as the step (2), it is preferably carried out only after the decomposition treatment of the protein by the protease having an exopeptidase activity as the step (2) in view of the yield of the deproteinized natural rubber latex and the operation efficiency of the  
15 deproteinization treatment.

In case the removing treatment of the protein and the decomposition product thereof is carried out by centrifugation, the protein and the decomposition product thereof are sufficiently removed by only one centrifugation  
20 treatment, but the centrifugation treatment may be carried out twice or more times as far as an adverse influence is exerted by loss of the rubber component and reduction in yield.

### [Surfactant]

In the method of preparing a deproteinized natural rubber of the present invention, a surfactant as a stabilizer is preferably added to the latex before subjecting to the decomposition treatment of the protein or during the treatment. In case the pH of the ammonia-treated latex is adjusted to a neutral range or the decomposition treatment of the protein is carried out, the addition of the surfactant is desired to prevent coagulation of the rubber component.

10        Examples of the surfactant include, but are not limited to, various anionic surfactants, nonionic surfactants and cationic surfactants, which have conventionally been known. Since almost any protease having an exopeptidase activity has an optimum pH in a neutral range, preferred are those which exhibit stable surface activity in a neutral range, specifically pH 6 to 9, and preferably pH 6.5 to 8.5.

      Examples of the surfactants, which can be used in the present invention include the same anionic surfactants, nonionic surfactants and cationic surfactants as described in 20 the preparation method (I) of the present invention. These surfactants can be used alone or in combination.

### (Other additives)

In the method of preparing the deproteinized natural rubber latex of the present invention, other additives may be 25 incorporated optionally similar to the preparation method (I)



of the present invention, in addition to the respective components described above.

[Degree of protein decomposition treatment and allergy]

In the case the protein was subjected to the decomposition treatment by the preparation method of the present invention, as described above, the protein and the protein decomposition product, which have a number-average molecular weight of 4500 or more, are not detected. According to more preferred conditions of the present invention, the protein can be decomposed to such a degree that the protein and the protein decomposition product, which have a number-average molecular weight of 2000 or more, more preferably 1500 or more, are not detected.

In the case the protein was subjected to the decomposition treatment by the preparation method of the present invention, the content index of the ~~allergie~~ allergenic protein measured by the RAST-inhibition method can be reduced to 10  $\mu\text{g/g}$  or less, preferably 5  $\mu\text{g/g}$  or less, and more preferably 2  $\mu\text{g/g}$  or less. As described in the term A, it is generally considered that allergy caused by the protein is less likely to occur, substantially, when the content index of the ~~allergie~~ allergenic protein is smaller than 10  $\mu\text{g/g}$  or less.

C. The method (III) of preparing a ~~deproteinized~~ low allergenic natural rubber latex of the present invention will be described.

The low ~~allergie~~ allergenic natural rubber of the present invention has a feature, as described above, that (18) it is a natural rubber obtained by a decomposition treatment of a protein, wherein the protein and a protein decomposition product, which have a number-average molecular weight  $\langle M_n \rangle$  of 4500 or more, are not detected. The present invention includes the following embodiments.

(19) The low ~~allergie~~ allergenic natural rubber described in the term (18), wherein a protein and a protein decomposition product, which have a number-average molecular weight of 2000 or more, and preferably 1500 or more, are not detected.

(20) The low ~~allergie~~ allergenic natural rubber described in the term (18), wherein a content index of an ~~allergie~~ allergenic protein capable of producing an IgE-class antibody in a human blood serum is 10  $\mu\text{g/g}$  or less.

(21) The low ~~allergie~~ allergenic natural rubber described in the term (20), wherein the content index of the ~~allergie~~ allergenic protein is 5  $\mu\text{g/g}$  or less.

In the present invention, in case the protein is subjected to the decomposition treatment to such a degree that the protein and the protein decomposition product, which have a number-average molecular weight  $\langle M_n \rangle$  of 4500 or more, are not detected, as described above, it is presumed that the

portion, which can serve as an antigen capable of producing an IgE-antibody against human serum, is sufficiently decomposed or denatured. It is considered that allergy caused by the protein is less likely to occur when the  
5 content of the ~~allergie~~ allergenic protein is 10  $\mu$ g or less per 1 g of a crude rubber as described above.

It can be said that the deproteinized natural rubber having very small content index of the ~~allergie~~ allergenic protein of the present invention substantially contains no  
10 allergen formed by the protein.

The low ~~allergie~~ allergenic natural rubber of the present invention is obtained by performing a decomposition treatment of a protein by using a protease having an exopeptidase activity in place of a conventionally used  
15 protease (proteolytic enzyme).

The low ~~allergie~~ allergenic natural ~~natural~~ rubber of the present invention has a feature that it is obtained by performing a decomposition treatment of a protein by a protease having an exopeptidase activity. Surprisingly, the  
20 protein can be decomposed to such a degree that the protein and the protein decomposition product, which have a number-average molecular weight  $\langle M_n \rangle$  of 4500 or more, do not substantially exist by performing a treatment using the protease.

25 [Method of preparing low ~~allergie~~ allergenic natural

rubber latex]

The low ~~allergie~~ allergenic natural rubber latex of the present invention is obtained by adding a protease having an exopeptidase activity or a mixture of two or more proteases  
5 in a natural rubber latex, aging the latex for several hours to about one week, and decomposing the protein in the latex.

More specifically, a protease having an exopeptidase activity is added in the amount of about 0.001 to 10% by weight based on the rubber solid content of the natural  
10 rubber latex, and then the latex is aged at 5 to 90°C, preferably 20 to 60°C, for several hours to about one week. The decomposition treatment of the protein may be carried out twice or more times, if necessary.

In the case the protease having an exopeptidase  
15 activity is added, it is preferred to previously adjust the pH of the latex to a neutral range, specifically pH 6 to 9, and more preferably pH 6.5 to 8.5, in consideration of the fact that almost any protease has an optimum pH in a neutral range (specifically pH 6 to 9) as described hereinafter. To  
20 adjust the pH of the latex to the neutral range, sodium dihydrogenphosphate, formalin, diluted hydrochloric acid or the like may be added.

The latex subjected to the decomposition treatment of the protein may be optionally subjected to a purification  
25 treatment (removing treatment) by centrifugation,

ultrafiltration of the like. In case the purification treatment (removing treatment) by ~~centraifugation~~ centrifugation is carried out, centrifugation may be carried out by a conventional method after adding the surfactant in the amount within a range from 0.01 to 10% by weight. Although the removing treatment is sufficiently carried out by only one centrifugation treatment, the centrifugation treatment may be carried out twice or more times to enhance the effect of removing the protein and the decomposition product thereof. Then, the rubber component is treated by a conventional method such as coagulation, drying and the like to obtain a deproteinized natural rubber.

The coagulation method includes acid coagulation which is generally carried out, and further salt coagulation, alcohol addition coagulation or freeze-drying and so on. Among these methods, acid coagulation is more preferable for large scale production since the efficiency is highest and the influence on properties of the resulting rubber is less.

[Raw latex]

As the natural rubber latex as a starting material for obtaining the deproteinized natural rubber latex of the present invention, the same one described in the preparation method (I) of the present invention can be used.

(Protease having exopeptidase activity)

The protease having an exopeptidase activity may also have an endopeptidase activity. In this case, the effect of reducing the molecular weight of the protein and the efficiency of the decomposition can be further improved. Accordingly, in order to prepare a low ~~allergie~~ allergenic natural rubber of the present invention, a protease having both an exoprotease activity and an endopeptidase activity is preferably used.

10 As the protease having an exopeptidase activity, the same one described in the preparation method (I) of the present invention can be used.

In the protein decomposition treatment for obtaining the low ~~allergie~~ allergenic natural rubber of the present invention, a protein decomposition treatment by a protease having an exopeptidase activity may be used in combination with a protein decomposition treatment by other proteases.

The other protease is not specifically limited, and examples thereof include various conventionally been known peptidases such as protease derived from filamentous bacteria (excluding protease having an exopeptidase activity) and protease derived from yeast shown in Table 1.

[Surfactant]

In the case the decomposition treatment of the protein is carried out to prepare a deproteinized natural rubber of the present invention, a surfactant as a stabilizer is preferably added to the latex before subjecting to the decomposition treatment of the protein or during the treatment. In the case the pH of the ammonia-treated latex is adjusted to a neutral range or the decomposition treatment of the protein is carried out, the addition of the surfactant is desired to prevent coagulation of the rubber component.

Examples of the surfactant include, but are not limited to, various anionic surfactants, nonionic surfactants and cationic surfactants, which have conventionally been known. Since almost any protease having an exopeptidase activity has an optimum pH in a neutral range, preferred are those which exhibit stable surface activity in a neutral range, specifically pH 6 to 9, and preferably pH 6.5 to 8.5.

Examples of the surfactants, which can be used in the present invention include the same anionic surfactants, nonionic surfactants and cationic surfactants as described in the preparation method (I) of the present invention. These surfactants can be used alone or in combination.

(Other additives)

In the method of preparing the deproteinized natural rubber latex of the present invention, other additives may be



incorporated optionally similar to the preparation method (I) of the present invention, in addition to the respective components described above.

[Amount of remained protein of natural rubber and  
5 allergy]

In the low ~~allergie~~ allergenic natural rubber latex (III) of the present invention, the protein is remained in the same amount as that of the natural rubber latex as control in case of comparing by the nitrogen content (N%) by  
10 the Kjeldahl's method.

However, the low ~~allergie~~ allergenic natural rubber latex of the present invention has a very small content of the protein having a large molecular weight and the ~~allergie~~ allergenic protein as compared with the deproteinized natural  
15 rubber latex subjected to the deproteinization treatment by a conventional method. Specifically, the protein and the protein decomposition product, which have a number-average molecular weight  $\langle M_n \rangle$  of 4500 or more, are not detected from the low ~~allergie~~ allergenic natural rubber latex obtained by  
20 the method of the present invention.

As is apparent from Comparative Examples described hereinafter, the protein and the protein decomposition product, which have a number-average molecular weight  $\langle M_n \rangle$  of 4500 or more, are detected from the deproteinized natural  
25 rubber latex subjected to the deproteinization treatment by a

conventional method (one enzyme treatment and one centrifugation treatment). On the other hand, as is apparent from Examples described hereinafter, the protein and the protein decomposition product, which have a number-average molecular weight  $\langle M_n \rangle$  of 4500 or more, are not detected from the natural rubber latex subjected to the protein decomposition treatment by the method of the present invention (one enzyme treatment and no centrifugation treatment).

As described above, the degree that the protein and the protein decomposition product, which have a number-average molecular weight  $\langle M_n \rangle$  of 4500 or more, are not detected means that the protein is decomposed to such a degree that allergy caused by the protein does not substantially occur.

Regarding the low ~~allergic~~ allergenic natural rubber latex of the present invention, although the total amount of the protein remained in the latex is large, a possibility of causing immediate allergy due to the protein is markedly reduced.

D. The method (IV) of preparing a deproteinized natural rubber latex of the present invention will be described.

The deproteinized natural rubber (IV) of the present invention has a feature, as described above, that (22) it is a natural rubber obtained by a decomposition treatment and a removing treatment of a protein, wherein the content of the

protein is 0.02% or less in terms of a nitrogen content, an absorption at  $3280\text{ cm}^{-1}$  is not recognized in an infrared absorption spectrum, and the protein and a protein decomposition product, which have a number-average molecular weight  $\langle \text{Mn} \rangle$  of 4500 or more, are not detected. The present invention includes the following embodiments.

(23) The deproteinized natural rubber described in the term (22), wherein a protein and a protein decomposition product, which have a number-average molecular weight of 2000 or more, and preferably 1500 or more, are not detected.

(24) The deproteinized natural rubber described in the term (22), wherein a content index of an ~~allergie~~ allergenic protein capable of producing an IgE-class antibody in a human serum is  $10\text{ }\mu\text{g/g}$  or less.

(25) The deproteinized natural rubber described in the term (22), wherein the content index of the ~~allergie~~ allergenic protein is  $5\text{ }\mu\text{g/g}$  or less.

In the case the protein is subjected to the decomposition treatment to such a degree that the protein and the protein decomposition product, which have a number-average molecular weight  $\langle \text{Mn} \rangle$  of 4500 or more, are not detected, as described above, it is presumed that the portion, which can serve as an antigen capable of producing an IgE-antibody against human serum, is sufficiently decomposed or denatured. It is considered that allergy

caused by the protein is less likely to occur when the content of the ~~allergie~~ allergenic protein is 10  $\mu$ g or less per 1 g of a crude rubber as described above.

It can be said that the deproteinized natural rubber  
5 having very small content index of the ~~allergie~~ allergenic protein of the present invention substantially contains no allergen formed by the protein.

The deproteinized natural rubber of the present invention is obtained by performing a decomposition treatment  
10 of a protein by a protease having an exopeptidase activity, along with a decomposition treatment of a protein by a conventionally used protease (proteolytic enzyme), and performing a removing treatment of the protein and the decomposition product thereof.

15 The deproteinized natural rubber of the present invention has a feature that it is obtained by performing a decomposition treatment of a protein by a protease having an exopeptidase activity, in addition to a decomposition treatment of a protein by a conventionally used protease  
20 (proteolytic enzyme), and performing a removing treatment of the protein and the decomposition product thereof. Surprisingly, the protein can be decomposed to such a degree that the protein and the protein decomposition product, which have a number-average molecular weight of 4500 or more, do  
25 not substantially exist by performing a treatment using the

protease.

[Method of preparing deproteinized natural rubber latex]

The deproteinized natural rubber latex of the present invention is obtained by the steps of:

- (1) subjecting a natural rubber latex to a decomposition treatment of a protein using a conventionally known protease (alkali protease),
- (2) optionally adjusting the pH of the latex to a neutral range and performing a decomposition treatment of a protein using a protease having an ~~exopeptidase~~ exopeptidase activity, and
- (3) removing the protein and the decomposition product thereof from the latex thus obtained, and coagulating the rubber component.

The deproteinized natural rubber can be obtained in the following procedure. First, a conventionally known alkali protease is added in the amount of about 0.001 to 10% by weight based on the rubber solid content of the natural rubber latex, and then the protein decomposition treatment is carried out by aging at 5 to 90°C, preferably 20 to 60°C, for several hours to about one week. After 0.01 to 10% by weight of a surfactant was optionally added, a protease having an exopeptidase activity is added in the amount of about 0.001 to 10% by weight based on the rubber solid

content of the latex, and then the protein decomposition treatment is carried out by aging at 5 to 90°C, preferably 20 to 60°C, for several hours to about one week.

In the case the protease having an exopeptidase activity is added, it is preferred to previously adjust the pH of the latex to a neutral range, specifically pH 6 to 9, and more preferably pH 6.5 to 8.5, in consideration of the fact that almost any protease has an optimum pH in a neutral range (specifically pH 6 to 9) as described hereinafter. To adjust the pH of the latex to the neutral range, sodium dihydrogenphosphate, formalin, diluted hydrochloric acid or the like may be added.

In the case the removing treatment is carried out by centrifugation, centrifugation may be carried out by a conventional method after adding the surfactant in the amount within a range from 0.01 to 10% by weight. Although the removing treatment is sufficiently carried out by only one centrifugation treatment, the centrifugation treatment may be carried out twice or more times to enhance the effect of removing the protein and the decomposition product thereof. Then, the rubber component is treated by a conventional method such as coagulation, drying and the like to obtain a deproteinized natural rubber.

The coagulation method includes acid coagulation which is generally carried out, and further salt coagulation,

alcohol addition coagulation or freeze-drying and so on. Among these methods, acid coagulation is more preferable for large scale production since the efficiency is highest and the influence on properties of the resulting rubber is less.

5 [Raw latex]

As the natural rubber latex as a starting material for obtaining the deproteinized natural rubber latex of the present invention, the same one described in the preparation method (I) of the present invention can be used.

10 [Protease]

The enzyme for decomposing a protein, which is used to prepare a deproteinized natural rubber of the present invention, includes two kinds of enzymes, such as a conventionally known protease (alkali protease) and a protease having an exopeptidase activity.

(Conventionally known protease)

The conventionally known protease is not specifically limited, and may be either a protease derived from filamentous bacteria or a protease derived from yeast. Among these proteases, a protease derived from bacteria is preferably used. In general, the protease derived from bacteria is a protease, which has an optimum pH in an alkali range and only has an endoprotease activity.

Specific examples of the protease derived from bacteria include proteases described in Table 1.

(Protease having exopeptidase activity)

The protease having an exopeptidase activity may also have an endopeptidase activity. In this case, the effect of reducing the molecular weight of the protein and the efficiency of the decomposition can be further improved.

When the protease having an exopeptidase activity is limited by its origin, as described above, the protease is preferably produced by microorganisms, which belong to the genus *Aspergillus* or *Rhizopus*, as a kind of filamentous bacteria. As the microorganisms, which belong to the genus *Aspergillus*, the same one described in the preparation method (I) of the present invention can be used.

[Surfactant]

In case the decomposition treatment of the protein is carried out to prepare a deproteinized natural rubber of the present invention, a surfactant as a stabilizer is preferably added to the latex before subjecting to the decomposition treatment of the protein or during the treatment. In case the pH of the ammonia-treated latex is adjusted to a neutral range or the decomposition treatment of the protein is carried out, the addition of the surfactant is desired to prevent coagulation of the rubber component.

Examples of the surfactant include, but are not limited to, various anionic surfactants, nonionic surfactants and cationic surfactants which have conventionally been known.



Since almost any protease having an exopeptidase activity has an optimum pH in a neutral range (specifically pH 6 to 9), preferred are those which exhibit stable surface activity in a neutral range, specifically pH 6 to 9, and preferably pH 6.5 to 8.5.

Examples of the surfactants, which can be used in the present invention include the same anionic surfactants, nonionic surfactants and cationic surfactants as described in the preparation method (I) of the present invention. These surfactants can be used alone or in combination.

(Other additives)

In the method of preparing the deproteinized natural rubber latex of the present invention, other additives may be incorporated optionally similar to the preparation method (I) of the present invention, in addition to the respective components described above.

#### EXAMPLES

The following Examples and Comparative Examples further illustrate the present invention, but the present invention is not limited by the following Examples.

In the following Examples and Comparative Examples, a field latex produced in Malaysia or a high ammonia natural rubber latex [rubber solid content: 60.2% by weight, ammonia content: 0.7%] manufactured by Soctex Co. (Malaysia) was used.

As the surfactant, a nonionic surfactant manufactured by Toho Chemical Industry Co., Ltd. under the trade name of "Triton X-100" was used.

[Preparation of low ~~allergie~~ allergenic natural rubber  
5 latex]

#### Example 1

(Only protein decomposition treatment)

To 100 parts by weight of a rubber content of a field latex, 1.0 parts by weight of a nonionic surfactant and 0.12%  
10 of sodium naphthenate were added, thereby to stabilize the latex, and then the pH of the latex was adjusted to 7.0 by using an aqueous 5% sodium dihydrogenphosphate solution. To 100 parts by weight of the rubber content of this latex, 0.1 parts by weight of a protease having an exopeptidase activity  
15 was added, and then the latex was aged by allowing to stand at 30°C for 24 hours to obtain a low ~~allergie~~ allergenic natural rubber latex which has been subjected to a protein decomposition treatment.

As the protease, a protease, which has both an  
20 exopeptidase activity and an endopeptidase activity and an optimum pH in a neutral range, and is also produced by microorganisms which belong to *Aspergillus oryzae* [manufactured by Amano Enzyme, Inc. under the trade name of "Umamizyme"], was used (see Table 2). This protease had a  
25 peptidase activity of 70 u/g or more (pH 7.0, LGG (L-Leucyl-

Glycyl-Glycine) method).

(Protein decomposition treatment and protein removing treatment)

The low ~~allergie~~ allergenic natural rubber latex which  
5 has been subjected to the protein decomposition treatment was  
diluted with an aqueous 1% solution of a nonionic surfactant,  
thereby to reduce the rubber content of the latex to 10%, and  
then subjected to a centrifugation treatment at 13000 rpm for  
30 minutes. The cream component thus separated in the upper  
10 layer was taken out and then dispersed again in the same  
amount of water to obtain a low ~~allergie~~ allergenic natural  
rubber latex which has been subjected to a protein  
decomposition treatment and a protein removing treatment.

#### Example 2

15 (Only protein decomposition treatment)

A high ammonia latex (hereinafter referred to as a "HA  
latex") was diluted so that the rubber content is reduced to  
30% by weight. To 100 parts by weight of a rubber content of  
the latex, 1.0 parts by weight of a nonionic surfactant and  
20 0.12% of sodium naphthenate (stabilizer) were added, thereby  
to stabilize the latex, and then the pH of the latex was  
adjusted to 7.0 by using an aqueous 5% sodium  
dihydrogenphosphate solution. To 100 parts by weight of the  
rubber content of this latex, 0.1 parts by weight of a  
25 protease (aforementioned "Umamizyme") was added, and then the

latex was aged by allowing to stand at 30°C for 24 hours to obtain a low ~~allergie~~ allergenic natural rubber latex which has been subjected to a protein decomposition treatment.

(Protein decomposition treatment and protein removing  
5 treatment)

The low ~~allergie~~ allergenic natural rubber latex which has been subjected to the protein decomposition treatment was diluted with an aqueous 1% solution of a nonionic surfactant, thereby to reduce the rubber content of the latex to 10%, and  
10 then subjected to a centrifugation treatment at 13000 rpm for 30 minutes. The cream component thus separated in the upper layer was taken out and then dispersed again in the same amount of water to obtain a low ~~allergie~~ allergenic natural rubber latex which has been subjected to a protein  
15 decomposition treatment and a protein removing treatment.

### Example 3

(Only protein decomposition treatment)

In the same manner as in Example 1 (namely, the field latex is used as a starting material), except that a protease  
20 produced by microorganisms which belong to *Aspergillus mellus* [manufactured by Amano Enzyme, Inc. under the trade name of P "Amano" 3G] was used as the protease having an exopeptidase activity in place of aforementioned "Umamizyme" and that the amount was changed to 0.1 parts by weight based on 100 parts  
25 by weight of the rubber content of the latex, the

decomposition treatment of the protein was carried out to obtain a low ~~allergie~~ allergenic natural rubber latex.

The protease P "Amano" 3G is a protease, which has a protein digestion potency of 10000 u/g or more (pH 7.0, Amano  
5 method) and has both an exopeptidase activity and an endopeptidase activity and also has an optimum pH in a neutral range as shown in Table 2.

(Protein decomposition treatment and protein removing treatment)

10 In the same manner as in Example 1, the low ~~allergie~~ allergenic natural rubber latex which has been subjected to the protein decomposition treatment was subjected to the dilution treatment, the centrifugation treatment and the redispersion treatment to obtain a low ~~allergie~~ allergenic  
15 natural rubber latex which has been subjected to a protein decomposition treatment and a protein removing treatment.

#### Example 4

(Only protein decomposition treatment)

In the same manner as in Example 2 (namely, the HA  
20 latex is used as a starting material), except that aforementioned P "Amano" 3G was used as the protease having an exopeptidase activity in place of aforementioned "Umamizyme" and that the amount was changed to 0.1 parts by weight based on 100 parts by weight of the rubber content of  
25 the latex, the decomposition treatment of the protein was

carried out to obtain a low ~~allergie~~ allergenic natural rubber latex.

(Protein decomposition treatment and protein removing treatment)

5        In the same manner as in Example 2, the low ~~allergie~~ allergenic natural rubber latex which has been subjected to the protein decomposition treatment was subjected to the dilution treatment, the centrifugation treatment and the redispersion treatment to obtain a low ~~allergie~~ allergenic  
10 natural rubber latex which has been subjected to a protein decomposition treatment and a protein removing treatment.

#### Example 5

(Only protein decomposition treatment)

In the same manner as in Example 1 (namely, the field  
15 latex is used as a starting material), except that a protease produced by microorganisms which belong to *Rhizopus oryzae* [manufactured by Amano Enzyme, Inc. under the trade name of "Peptidase R"] was used as the protease having an exopeptidase activity in place of aforementioned "Umamizyme"  
20 and that the amount was changed to 0.1 parts by weight based on 100 parts by weight of the rubber content of the latex, the decomposition treatment of the protein was carried out to obtain a low ~~allergie~~ allergenic natural rubber latex.

The protease "Peptidase R" is a protease, which has a  
25 peptidase activity of 420 u/g or more (pH 7.0, LGG method)

and has both an exopeptidase activity and an endopeptidase activity and also has an optimum pH in a neutral range as shown in Table 2.

(Protein decomposition treatment and protein removing  
5 treatment)

In the same manner as in Example 1, the low ~~allergie~~  
allergenic natural rubber latex which has been subjected to  
the protein decomposition treatment was subjected to the  
dilution treatment, the centrifugation treatment and the  
10 redispersion treatment to obtain a low ~~allergie~~ allergenic  
natural rubber latex which has been subjected to a protein  
decomposition treatment and a protein removing treatment.

#### Example 6

(Only protein decomposition treatment)

15 In the same manner as in Example 2 (namely, the HA  
latex is used as a starting material), except that  
aforementioned "Peptidase R" was used as the protease having  
an exopeptidase activity in place of aforementioned  
"Umamizyme" and that the amount was changed to 0.1 parts by  
20 weight based on 100 parts by weight of the rubber content of  
the latex, the decomposition treatment of the protein was  
carried out to obtain a low ~~allergie~~ allergenic natural  
rubber latex.

(Protein decomposition treatment and protein removing  
25 treatment)

In the same manner as in Example 2, the low ~~allergie~~  
allergenic natural rubber latex which has been subjected to  
the protein decomposition treatment was subjected to the  
dilution treatment, the centrifugation treatment and the  
5 redispersion treatment to obtain a low ~~allergie~~ allergenic  
natural rubber latex which has been subjected to a protein  
decomposition treatment and a protein removing treatment.

#### Comparative Example 1

(Only protein decomposition treatment)

10 To 100 parts by weight of a rubber content of a field  
latex, 0.1 parts by weight of an alkali protease, 1.0 parts  
by weight of a nonionic surfactant and 0.12% of sodium  
naphthenate were added, thereby to stabilize the latex.

As the alkali protease, a protease, which is derived  
15 from bacteria and is also produced by microorganisms which  
belong to *Bacillus licheniformis* [manufactured by Novo-  
Nordisk Bioindustri A/S under the trade name of "Alcalase  
2.0M"], was used. This alkali protease had a potency of 2.0  
AU/g (pH 8.3) and has an optimum pH in an alkali range, as  
20 shown in Table 1, and also has an endopeptidase but has no  
exopeptidase activity.

After adjusting the pH to 9.2 by using sodium  
dihydrogenphosphate, the latex was aged by allowing to stand  
at 30°C for 24 hours to obtain a natural rubber latex which  
25 has been subjected to a protein decomposition treatment.



(Protein decomposition treatment and protein removing treatment)

The low ~~allergie~~ allergenic natural rubber latex which has been subjected to the protein decomposition treatment was  
5 diluted with an aqueous 1% solution of a nonionic surfactant, thereby to reduce the rubber content of the latex to 10%, and then subjected to a centrifugation treatment at 13000 rpm for 30 minutes. The cream component thus separated in the upper layer was taken out and then dispersed again in the same  
10 amount of water to obtain a natural rubber latex which has been subjected to a protein decomposition treatment and a protein removing treatment.

[Evaluation of protein decomposition treatment]

(Measurement of nitrogen content)

15 Using each of latexes prepared by dispersing again a cream component formed after the centrifugation in water in Examples 1 to 6 and Comparative Example 1, and the latex was spread over a glass plate to obtain a cast film.

20 These cast films were used as samples for measuring the nitrogen content.

With respect to Example 1 and Comparative Example 1, same cast films as those described above were made by using latexes subjected only to the protein decomposition treatment and these films were used as samples for measuring the  
25 nitrogen content.

Furthermore, cast films were made directly from the field latex and HA latex, which has been subjected to neither protein decomposition treatment nor washing treatment, and these films were used as samples of control.

5        With respect to respective samples of Examples 1 to 6, Comparative Example 1 and control, the nitrogen content (N%) was measured by a RRIM test method (Rubber Research Institute of Malaysia (1973). 'SMR Bulletin No. 7').

10       The measurement results of the nitrogen content (N%) are shown in Table 3.

(Measurement of content index of ~~allergie~~ allergenic protein)

15       According to a RAST-inhibition method, a content index of an ~~allergie~~ allergenic protein contained in each of the natural rubber latexes obtained in Examples 1 to 6 and Comparative Example 1 was measured. The "content index of the ~~allergie~~ allergenic protein" was measured by a Competitive immunoinhibition method using aforementioned Pharmacia Cap system in Deutsche BGFA  
20       (Berufsgenossenschaftliches Forschungsinstitut für Arbeitsmedizin).

25       In Example 1 and Comparative Example 1, the content index of the ~~allergie~~ allergenic protein was calculated in the same manner, also with respect to the latex which has been subjected only to the protein decomposition treatment.

The measurement results of the content index of the ~~allergie~~ allergenic protein are shown in Table 3.

{Table 3} Table 3

Kinds of latex	Protease		Protein removing treatment	Nitrogen content (N%)	Content index of allergic allergenic protein
	Kind	Amount*1 (parts by weight)			
Example 1	Field latex	Umamizyme	0.1	no	0.643
				yes	0.062
Example 2	HA latex	Umamizyme	0.1	yes	0.041
Example 3	Field latex	P "Amano" 3G	0.1	yes	0.061
Example 4	HA latex	P "Amano" 3G	0.1	yes	0.042
Example 5	Field latex	Peptidase R	0.1	yes	0.062
Example 6	HA latex	Peptidase R	0.1	yes	0.042
Comp. Example 1	Field latex	Alcalase 2.0M	0.1	no	0.645
				yes	0.062
Control 1	Field latex	--	-	yes*2	0.654
Control 2	HA latex		-	yes*2	0.334
					>8000 $\mu\text{g/g}$
					1060 $\mu\text{g/g}$

\*1: Amount (parts by weight) of protease is a value based on 100 parts by weight of the rubber content of the latex.

\*2: Protein is merely removed by concentration.

As is apparent from Table 3, although the low ~~allergie~~  
allergenic natural rubber latex of Example 1 has the same  
nitrogen content (N%) as that of the deproteinized natural  
rubber latex of Comparative Example 1 obtained by a  
5 conventional treatment using an enzyme, the content index of  
the ~~allergie~~ allergenic protein was markedly reduced.

In Example 1, the content index of the ~~allergie~~  
allergenic protein was markedly reduced as compared with a  
conventional HA latex shown in control 2 even when subjected  
10 only to an enzyme treatment, and also reduced as compared  
with that which has been subjected to a conventional enzyme  
treatment (latex of Comparative Example 1 which has not been  
subjected to a protein removing treatment).

Therefore, it has been found that a possibility of  
15 causing allergy due to the protein is markedly reduced.

(Analysis of molecular weight of protein)

With respect to the natural rubber latexes obtained in  
Example 1 and Comparative Example 1, it was analyzed whether  
or not impurities having a number-average molecular weight  
20 <Mn> within a range from 4500 to 4700 exist, using an  
analysis system of a protein, comprising a combination of a  
time of flight (TOF) type mass spectrometer and a two-  
dimensional surface decorative chip [for example, protein  
structure analyzer "Protein Chip<sup>TM</sup> System", manufactured by  
25 CIPHERGEN Biosystems, Inc.]

The analysis of the molecular weight of the protein by the above "Protein Chip™ System" was carried out in the following procedure. (1) First, a sample of serosity of a natural rubber latex was adsorbed on a chip, (2) the chip is washed with a washing buffer so that only the adsorbed protein is remained, (3) an energy absorbing substance is applied on the adsorbed protein, (4) the protein on the chip is ionized by irradiating with laser beam, and (5) the molecular weight was measured by using a TOF type mass spectrograph.

With respect to the analysis results of the number-average molecular weight  $\langle M_n \rangle$  about the remained protein and protein decomposition product, the measurement results of samples of Example 1 obtained from the low ~~allergie~~ allergenic natural rubber latex subjected only to the protein decomposition treatment are shown in Fig. 1, the measurement results of samples of Example 1 obtained from the low ~~allergie~~ allergenic natural rubber latex which has been subjected to the protein decomposition treatment and the protein removing treatment are shown in Fig. 2, and the measurement results of samples of Comparative Example 1 obtained from the deproteinized natural rubber latex by a conventional treatment using an enzyme are shown in Fig. 3, respectively.

The molecular weight of control samples obtained from

the HA latex, which has been subjected to neither protein decomposition treatment nor protein removing treatment, was analyzed. The measurement results are shown in Fig. 10.

As is apparent from the measurement results of the analysis of the molecular weight, in Comparative Example 1 (Fig. 3), a peak existed at the position (position corresponding to the existence of the protein) where the number-average molecular weight  $\langle M_n \rangle$  is about 4700. To the contrary, in both cases where only the protein decomposition treatment was carried out (Fig. 1) and the removing treatment of the protein and the decomposition product was further carried out (Fig. 2) of Example 1, a peak was not observed in the range where the number-average molecular weight  $\langle M_n \rangle$  is about 4500 or more. In case where the removing treatment of the protein and the decomposition product was further carried out, in addition to the protein decomposition treatment (Fig. 2), a peak was not observed in the range where the number-average molecular weight  $\langle M_n \rangle$  is from 1500 to 4500.

[Preparation of ~~deprotenized~~ deproteinated natural rubber latex]

#### Example 7

(Decomposition of protein by alkali protease)

To 100 parts by weight of a rubber content of a field latex, 1.0 parts by weight of a nonionic surfactant and 0.12% of sodium naphthenate were added, thereby to stabilize the

latex. To 100 parts by weight of the rubber content of this latex, 0.1 parts by weight of an alkali protease was added, and then the latex was aged by allowing to stand at 30°C for 24 hours.

5        As the alkali protease, a protease, which is a protease derived from bacteria and is produced by microorganisms which belong to *Bacillus licheniformis* as a kind of bacteria of the genus *Bacillus* [manufactured by Novo-Nordisk Bioindustri A/S under the trade name of "Alcalase 2.0M"], was used. This  
10       alkali protease had a potency of 2.0 AU/g (pH 8.3) and has an optimum pH in an alkali range, as shown in Table 1, and also has an endopeptidase but has no exopeptidase activity.

(Decomposition of protein by protease having exopeptidase activity)

15       To the aged latex, an aqueous 5% sodium dihydrogenphosphate solution was added, thereby to adjust the pH to 7.0. To 100 parts by weight of the rubber content of the latex, 0.1 parts by weight of a protease having an exopeptidase activity was added. After the addition of the  
20       protease, the latex was aged again by allowing to stand at 30°C for 24 hours.

      As the protease, a protease, which has both an exopeptidase activity and an endopeptidase activity and an optimum pH in a neutral range, and is also produced by  
25       microorganisms which belong to *Aspergillus oryzae*



[manufactured by Amano Enzyme, Inc. under the trade name of "Umamizyme"], was used (see Table 2). This protease had a peptidase activity of 70 u/g or more (pH 7.0, LGG (L-Leucyl-Glycyl-Glycine) method).

5 (Removal of protein and decomposition product thereof)

After the completion of the enzyme treatment, the latex was diluted with an aqueous 1% solution of a nonionic surfactant, thereby to reduce the rubber content of the latex to 10%, and then subjected to a centrifugation treatment at  
10 13000 rpm for 30 minutes. The cream component thus separated in the upper layer was diluted again and then subjected to the second centrifugation treatment in the same manner as described above.

The resulting cream component was dispersed again in  
15 water to obtain a deproteinized natural rubber latex.

#### Example 8

(Decomposition of protein by alkali protease)

A high ammonia latex (hereinafter referred to as a "HA latex") was diluted so that so that the rubber content is  
20 reduced to 30% by weight. To 100 parts by weight of a rubber content of a field latex, 1.0 parts by weight of a nonionic surfactant and 0.12% of sodium naphthenate were added, thereby to stabilize the latex. To 100 parts by weight of the rubber content of this latex, 0.1 parts by weight of an  
25 alkali protease (aforementioned "Alcalase 2.0M") was added,

and then the latex was aged by allowing to stand at 30°C for 24 hours.

(Decomposition of protein by protease having exopeptidase activity)

5        To the aged latex, an aqueous 5% sodium dihydrogenphosphate solution was added, thereby to adjust the pH to 7.0. To 100 parts by weight of the rubber content of the latex, 0.1 parts by weight of a protease having an exopeptidase activity (aforementioned "Umamizyme") was added.  
10      After the addition of the protease, the latex was aged again by allowing to stand at 30°C for 24 hours.

(Removal of protein and decomposition product thereof)

After the completion of the enzyme treatment, the latex was diluted with an aqueous 1% solution of a nonionic  
15      surfactant, thereby to reduce the rubber content of the latex to 10%, and then subjected to a centrifugation treatment at 13000 rpm for 30 minutes.

The cream component thus separated in the upper layer was diluted again and then subjected to the second  
20      centrifugation treatment in the same manner as described above.

The resulting cream component was dispersed again in water to obtain a deproteinized natural rubber latex.

#### Example 9

25        (Decomposition of protein by alkali protease)

In the same manner as in case of the "decomposition of the protein by the alkali protease" of Example 7, the protein in the field latex was decomposed by the alkali protease (aforementioned "Alcalase 2.0M").

5       (Decomposition of protein by protease having exopeptidase activity)

In the same manner as in case of the "decomposition of the protein by the protease having an exopeptidase activity" of Example 7, except that a protease produced by  
10 microorganisms which belong to *Aspergillus mellus* [manufactured by Amano Enzyme, Inc. under the trade name of P "Amano" 3G] was used as the protease having an exopeptidase activity in place of aforementioned "Umamizyme" and that the amount was changed to 0.1 parts by weight based on 100 parts  
15 by weight of the rubber content of the latex, the decomposition treatment of the protein was carried out.

The protease P "Amano" 3G is a protease, which has a protein digestion potency of 10000 u/g or more (pH 7.0, Amano method) and has both an exopeptidase activity and an  
20 endopeptidase activity and also has an optimum pH in a neutral range as shown in Table 2.

(Removal of protein and decomposition product thereof)

In the same manner as in case of the "removal of the protein and the decomposition product thereof" of Example 7,  
25 except that the latex was used after the completion of the

enzyme treatment by the protease P "Amano" 3G, the centrifugation treatment was carried out to obtain a deproteinized natural rubber latex.

#### Example 10

##### 5 (Decomposition of protein by alkali protease)

In the same manner as in case of the "decomposition of the protein by the alkali protease" of Example 8, the protein in the HA latex was decomposed by the alkali protease (aforementioned "Alcalase 2.0M").

##### 10 (Decomposition of protein by protease having exopeptidase activity)

In the same manner as in case of the "decomposition of the protein by the protease having an exopeptidase activity" of Example 8, except that aforementioned P "Amano" 3G was  
15 used as the protease having an exopeptidase activity in place of aforementioned "Umamizyme" and that the amount was changed to 0.1 parts by weight based on 100 parts by weight of the rubber content of the latex, the decomposition treatment of the protein was carried out.

##### 20 (Removal of protein and decomposition product thereof)

In the same manner as in case of the "removal of the protein and the decomposition product thereof" of Example 8, except that the latex was used after the completion of the enzyme treatment by the protease P "Amano" 3G, the  
25 centrifugation treatment was carried out to obtain a

deproteinized natural rubber latex.

Example 11

(Decomposition of protein by alkali protease)

In the same manner as in case of the "decomposition of  
5 the protein by the alkali protease" of Example 8, the protein  
in the field latex was decomposed by the alkali protease  
(aforementioned "Alcalase 2.0M").

(Decomposition of protein by protease having  
exopeptidase activity)

10 In the same manner as in case of the "decomposition of  
the protein by the protease having an exopeptidase activity"  
of Example 8, except that a protease produced by  
microorganisms which belong to *Rhizopus oryzae* [manufactured  
by Amano Enzyme, Inc. under the trade name of "Peptidase R"]  
15 was used as the protease having an exopeptidase activity in  
place of aforementioned "Umamizyme" and that the amount was  
changed to 0.1 parts by weight based on 100 parts by weight  
of the rubber content of the latex, the decomposition  
treatment of the protein was carried out.

20 The protease "Peptidase R" is a protease, which has a  
peptidase activity of 420 u/g or more (pH 7.0, LGG method)  
and has both an exopeptidase activity and an endopeptidase  
activity and also has an optimum pH in a neutral range as  
shown in Table 2.

25 (Removal of protein and decomposition product thereof)

In the same manner as in case of the "removal of the protein and the decomposition product thereof" of Example 8, except that the latex was used after the completion of the enzyme treatment by the protease "Peptidase R", the centrifugation treatment was carried out to obtain a deproteinized natural rubber latex.

#### Example 12

(Decomposition of protein by alkali protease)

In the same manner as in case of the "decomposition of the protein by the alkali protease" of Example 8, the protein in the field latex was decomposed by the alkali protease (aforementioned "Alcalase 2.0M").

(Decomposition of protein by protease having exopeptidase activity)

In the same manner as in case of the "decomposition of the protein by the protease having an exopeptidase activity" of Example 8, except that aforementioned "Peptidase R" was used as the protease having an exopeptidase activity in place of aforementioned "Umamizyme" and that the amount was changed to 0.1 parts by weight based on 100 parts by weight of the rubber content of the latex, the decomposition treatment of the protein was carried out.

(Removal of protein and decomposition product thereof)

In the same manner as in case of the "removal of the protein and the decomposition product thereof" of Example 8,

except that the latex was used after the completion of the enzyme treatment by the protease "Peptidase R", the centrifugation treatment was carried out to obtain a deproteinized natural rubber latex.

5           Comparative Example 2

A deproteinized natural rubber latex was prepared according to the method described in Japanese Patent No. 2,905,005.

10           A HA latex was diluted so that the rubber content is reduced to 30% by weight. To 100 parts by weight of a rubber content of a field latex, 0.1 parts by weight of an alkali protease, 1.0 parts by weight of a nonionic surfactant and 0.12% of sodium naphthenate were added, thereby to stabilize the latex.

15           As the alkali protease, a protease, which is a protease derived from bacteria and is produced by microorganisms which belong to *Bacillus licheniformis* as a kind of bacteria of the genus *Bacillus* [manufactured by Novo-Nordisk Bioindustri A/S under the trade name of "Alcalase 2.0M"], was used. This  
20           alkali protease had a potency of 2.0 AU/g (pH 8.3) and has an optimum pH in an alkali range, as shown in Table 1, and also has an endopeptidase but has no exopeptidase activity.

          After adjusting the pH to 9.2 by using sodium dihydrogenphosphate, the latex was aged by allowing to stand  
25           at 30°C for 24 hours.

After the completion of the enzyme treatment, the latex was diluted with an aqueous 1% solution of a nonionic surfactant, thereby to reduce the rubber content of the latex to 10%, and then subjected to a centrifugation treatment at 13000 rpm for 30 minutes. The cream component thus separated in the upper layer was dispersed again in water to obtain a deproteinized natural rubber latex.

[Evaluation of protein decomposition treatment]

(Measurement of nitrogen content)

Using each of latexes prepared by dispersing again a cream component formed after the centrifugation treatment in Examples 7 to 12 and Comparative Example 2 in water, and the latex was spread over a glass plate to obtain a cast film.

These cast films were used as samples for measuring the nitrogen content.

Furthermore, cast films were made directly from the HA latex, which has been subjected to neither protein decomposition treatment nor washing treatment, and these films were used as samples of control.

With respect to respective samples of Examples 7 to 12, Comparative Example 2 and control, the nitrogen content (N%) was measured by a RRIM test method (Rubber Research Institute of Malaysia (1973). 'SMR Bulletin No. 7').

The measurement results of the nitrogen content (N%) are shown in Table 4.



(Measurement of content index of ~~allergie~~ allergenic protein)

According to a RAST-inhibition method, a content index of an ~~allergie~~ allergenic protein contained in each of the  
5 natural rubber latexes obtained in Examples 7 to 12 and Comparative Example 2 was measured. The "content index of the ~~allergie~~ allergenic protein" was measured by a competitive immunity inhibition method using aforementioned Pharmacia Cap system in Deutsche BGFA  
10 (Berufsgenossenschaftliches Forschungsinstitut für Arbeitsmedizin).

Also with respect to the deproteinized natural rubber latexes obtained in Examples 7 to 12 and Comparative Example 2 as measuring samples in the same manner, the amount of the  
15 residual antibody was determined and the content index of the ~~allergie~~ allergenic protein was calculated.

The measurement results of the content index of the ~~allergie~~ allergenic protein are shown in Table 4.

[Table 4]

Kinds of latex	Protein decomposition decomposition treatment			Nitrogen content (N%)	Content index of allergenic protein
	Kind of protease	Amount (parts by weight)			
Example 7 Field latex	1) Alcalase	1) 0.1		0.018	2.1 $\mu\text{g/g}$
	2) Umamizyme	2) 0.1			
Example 8 HA latex	1) Alcalase	1) 0.1		0.012	n.d
	2) Umamizyme	2) 0.1			
Example 9 Field latex	1) Alcalase	1) 0.1		0.017	n.d
	2) P "Amano" 3G	2) 0.1			
Example 10 HA latex	1) Alcalase	1) 0.1		0.011	n.d
	2) P "Amano" 3G	2) 0.1			
Example 11 Field latex	1) Alcalase	1) 0.1		0.018	n.d
	2) Peptidase R	2) 0.1			
Example 12 HA latex	1) Alcalase	1) 0.1		0.011	n.d
	2) Peptidase R	2) 0.1			
Comp. Example 2 HA latex	Alcalase 2.0M	0.1		0.012	11.1 $\mu\text{g/g}$
Control HA latex	-	-		0.334	1060 $\mu\text{g/g}$

\*: The terms 1) and 2) in the column of the protein decomposition treatment denote the treatment by an alkali protease and the treatment by a protease having an exopeptidase activity, respectively

\*: Amount (parts by weight) of protease is a value based on 100 parts by weight of the rubber content of the latex.

\*: n.d. denotes a value lower than a detection limit ( $2 \mu\text{g/g}$ ).

As is apparent from Table 4, although the deproteinized natural rubbers of Examples 7 to 12 have the same nitrogen content (N%) as that of the deproteinized natural rubber of Comparative Example 2, the content index of the ~~allergie~~  
5 allergenic protein was markedly low and, therefore, a possibility of causing allergy due to the protein is markedly reduced. It has been found that, in Examples 8 to 12, the rubbers are deproteinized to such a degree that the ~~allergie~~  
allergenic protein can not be detected.

10 (Analysis of molecular weight of protein)

With respect to the natural rubber latexes obtained in Examples 7 to 10 and Comparative Example 2, it was analyzed whether or not impurities having a number-average molecular weight  $\langle M_n \rangle$  within a range from 4500 to 4700 exist, using an  
15 analysis system of a protein, comprising a combination of a time of flight (TOF) type mass spectrometer and a two-dimensional surface decorative chip [for example, protein structure analyzer "Protein Chip<sup>TM</sup> System", manufactured by CIPHERGEN Biosystems, Inc.] .

20 The analysis of the molecular weight of the protein by the above "Protein Chip<sup>TM</sup> System" was carried out in the following procedure. (1) First, a sample of serosity of a natural rubber latex was adsorbed on a chip, (2) the chip is washed with a washing buffer so that only the adsorbed  
25 protein is remained, (3) an energy absorbing substance is

applied on the adsorbed protein, (4) the protein on the chip is ionized by irradiating with laser beam, and (5) the molecular weight was measured by using a TOF type mass spectrograph.

5           With respect to the analysis results of the number-average molecular weight  $\langle M_n \rangle$  about the remained protein and protein decomposition product, the measurement results of samples obtained from the deproteinized natural rubber latex of Example 7 are shown in Fig. 5, the measurement results of  
10 samples obtained from the deproteinized natural rubber latex of Example 8 are shown in Fig. 7, the measurement results of samples obtained from the deproteinized natural rubber latex of Example 9 are shown in Fig. 6, the measurement results of samples obtained from the deproteinized natural rubber latex  
15 of Example 10 are shown in Fig. 8, and the measurement results of samples obtained from the deproteinized natural rubber latex of Comparative Example 2 by a conventional treatment using an enzyme are shown in ~~Fig. 9~~, Fig. 3, respectively.

20           The molecular weight of control samples obtained from the HA latex, which has been subjected to neither protein decomposition treatment nor protein removing treatment, was analyzed. The measurement results are shown in ~~Fig. 10~~ Fig. 4.

25           As is apparent from the measurement results of the

analysis of the molecular weight, in Comparative Example 2 (Fig. ~~9~~ Fig. 3), a peak existed at the position (position corresponding to the existence of the protein) where the number-average molecular weight  $\langle M_n \rangle$  is about 4700. To the contrary, in Example 7 (Fig. 5) and Example 9 (Fig. 6), a peak was not observed in the range where the number-average molecular weight  $\langle M_n \rangle$  is about 2000 or more. In Example 8 (Fig. 7) and Example 10 (Fig. ~~4~~ Fig. 8), a peak was not observed in the range where the number-average molecular weight  $\langle M_n \rangle$  is 4500 or more.

[Preparation of low allergie allergenic natural rubber]

#### Example 13

(Only protein decomposition treatment)

To 100 parts by weight of a rubber content of a field latex, 1.0 parts by weight of a nonionic surfactant and 0.12% of sodium naphthenate were added, thereby to stabilize the latex, and then the pH of the latex was adjusted to 7.0 by using an aqueous 5% sodium dihydrogenphosphate solution. To 100 parts by weight of the rubber content of this latex, 0.1 parts by weight of a protease having an exopeptidase activity was added, and then the latex was aged by allowing to stand at 30°C for 24 hours to obtain a low allergie allergenic natural rubber latex which has been subjected to a protein decomposition treatment.

As the protease, a protease, which has both an

exopeptidase activity and an endopeptidase activity and an optimum pH in a neutral range, and is also produced by microorganisms which belong to *Aspergillus oryzae* [manufactured by Amano Enzyme, Inc. under the trade name of "Umamizyme"], was used (see Table 2). This protease had a peptidase activity of 70  $\mu$ /g or more (pH 7.0, LGG (L-Leucyl-Glycyl-Glycine) method).

Furthermore, the rubber component of the low allergic allergenic natural rubber latex thus obtained was coagulated and dried to obtain a low allergic allergenic natural rubber latex which has been subjected to a protein decomposition treatment.

The coagulation was carried out according to acid coagulation method. The solid content of the latex obtained above was adjusted to 10 %, and then formic acid (87%) was added to coagulate the rubber component. The resulting rubber containing water to a great content was passed through rollers under cleaning to remove a large portion of water and to give a rubber sheet. The resulting rubber sheet was air-dried for 4 days and finally dried in oven at 60°C for 3 days to obtain the solid rubber. In the following Examples and Reference Examples, solid rubbers were obtained according to the same method stated above.

(Protein decomposition treatment and protein removing treatment)

The low ~~allergie~~ allergenic natural rubber latex which has been subjected to the protein decomposition treatment was diluted with an aqueous 1% solution of a nonionic surfactant, thereby to reduce the rubber content of the latex to 10%, and  
5 then subjected to a centrifugation treatment at 13000 rpm for 30 minutes. The cream component thus separated in the upper layer was taken out and then dispersed again in the same amount of water to obtain a low ~~allergie~~ allergenic natural rubber latex which has been subjected to a protein  
10 decomposition treatment and a protein removing treatment.

Furthermore, the cream component was dried to obtain a low ~~allergie~~ allergenic natural rubber latex which has been subjected to a protein decomposition treatment and a protein removing treatment.

15        Example 14

(Only protein decomposition treatment)

A high ammonia latex (hereinafter referred to as a "HA latex") was diluted so that the rubber content is reduced to 30% by weight. To 100 parts by weight of a rubber content of  
20 the latex, 1.0 parts by weight of a nonionic surfactant and 0.12% of sodium naphthenate (stabilizer) were added, thereby to stabilize the latex, and then the pH of the latex was adjusted to 7.0 by using an aqueous 5% sodium dihydrogenphosphate solution. To 100 parts by weight of the  
25 rubber content of this latex, 0.1 parts by weight of a



protease (aforementioned "Umamizyme") was added, and then the latex was aged by allowing to stand at 30°C for 24 hours to obtain a low ~~allergie~~ allergenic natural rubber latex which has been subjected to a protein decomposition treatment.

5        Furthermore, the rubber component of the low ~~allergie~~ allergenic natural rubber latex thus obtained was coagulated and dried to obtain a low ~~allergie~~ allergenic natural rubber latex which has been subjected to a protein decomposition treatment.

10        (Protein decomposition treatment and protein removing treatment)

      The low ~~allergie~~ allergenic natural rubber latex which has been subjected to the protein decomposition treatment was diluted with an aqueous 1% solution of a nonionic surfactant, 15        thereby to reduce the rubber content of the latex to 10%, and then subjected to a centrifugation treatment at 13000 rpm for 30 minutes. The cream component thus separated in the upper layer was taken out and then dispersed again in the same amount of water to obtain a low ~~allergie~~ allergenic natural 20        rubber latex which has been subjected to a protein decomposition treatment and a protein removing treatment.

      Furthermore, the cream component was dried to obtain a low ~~allergie~~ allergenic natural rubber latex which has been subjected to a protein decomposition treatment and a protein 25        removing treatment.

## Example 15

(Only protein decomposition treatment)

In the same manner as in Example 13 (namely, the field latex is used as a starting material), except that a protease  
 5 produced by microorganisms which belong to *Aspergillus mellus* [manufactured by Amano Enzyme, Inc. under the trade name of P "Amano" 3G] was used as the protease having an exopeptidase activity in place of aforementioned "Umamizyme" and that the amount was changed to 0.1 parts by weight based on 100 parts  
 10 by weight of the rubber content of the latex, the decomposition treatment of the protein was carried out to obtain a low ~~allergie~~ allergenic natural rubber latex.

The protease P "Amano" 3G is a protease, which has a protein digestion potency of 10000 u/g or more (pH 7.0, Amano  
 15 method) and has both an exopeptidase activity and an endopeptidase activity and also has an optimum pH in a neutral range as shown in Table 2.

Furthermore, the rubber ~~allergie~~ allergenic component of the low ~~allergie~~ allergenic natural rubber latex thus  
 20 obtained was coagulated and dried to obtain a low ~~allergie~~ allergenic natural rubber latex which has been subjected to a protein decomposition treatment.

(Protein decomposition treatment and protein removing treatment)

25 In the same manner as in Example 13, the low ~~allergie~~

allergenic natural rubber latex which has been subjected to the protein decomposition treatment by the protease P "Amano" 3G was subjected to the dilution treatment, the centrifugation treatment and the redispersion treatment to  
5 obtain a low ~~allergie~~ allergenic natural rubber latex which has been subjected to a protein decomposition treatment and a protein removing treatment.

Furthermore, the cream component was dried to obtain a low ~~allergie~~ allergenic natural rubber latex which has been  
10 subjected to a protein decomposition treatment and a protein removing treatment.

#### Example 16

(Only protein decomposition treatment)

In the same manner as in Example 14 (namely, the HA  
15 latex is used as a starting material), except that aforementioned P "Amano" 3G was used as the protease having an exopeptidase activity in place of aforementioned "Umamizyme" and that the amount was changed to 0.1 parts by weight based on 100 parts by weight of the rubber content of  
20 the latex, the decomposition treatment of the protein was carried out to obtain a low ~~allergie~~ allergenic natural rubber latex.

Furthermore, the rubber component of the low ~~allergie~~ allergenic natural rubber latex thus obtained was coagulated  
25 and dried to obtain a low ~~allergie~~ allergenic natural rubber

latex which has been subjected to a protein decomposition treatment.

(Protein decomposition treatment and protein removing treatment)

5        In the same manner as in Example 14, the low ~~allergie~~  
allergenic natural rubber latex which has been subjected to  
the protein decomposition treatment by the protease P "Amano"  
3G was subjected to the dilution treatment, the  
centrifugation treatment and the redispersion treatment to  
10 obtain a low ~~allergie~~ allergenic natural rubber latex which  
has been subjected to a protein decomposition treatment and a  
protein removing treatment.

Furthermore, the cream component was dried to obtain a  
low ~~allergie~~ allergenic natural rubber latex which has been  
15 subjected to a protein decomposition treatment and a protein  
removing treatment.

#### Example 17

(Only protein decomposition treatment)

In the same manner as in Example 13 (namely, the field  
20 latex is used as a starting material), except that a protease  
produced by microorganisms which belong to *Rhizopus oryzae*  
[manufactured by Amano Enzyme, Inc. under the trade name of  
"Peptidase R"] was used as the protease having an  
exopeptidase activity in place of aforementioned "Umamizyme"  
25 and that the amount was changed to 0.1 parts by weight based

on 100 parts by weight of the rubber content of the latex, the decomposition treatment of the protein was carried out to obtain a low ~~allergie~~ allergenic natural rubber latex.

The protease "Peptidase R" is a protease, which has a  
5 peptidase activity of 420 u/g or more (pH 7.0, LGG method) and has both an exopeptidase activity and an endopeptidase activity and also has an optimum pH in a neutral range as shown in Table 2.

Furthermore, the rubber component of the low ~~allergie~~  
10 allergenic natural rubber latex thus obtained was coagulated and dried to obtain a low ~~allergie~~ allergenic natural rubber latex which has been subjected to a protein decomposition treatment.

(Protein decomposition treatment and protein removing  
15 treatment)

In the same manner as in Example 13, the low ~~allergie~~ allergenic natural rubber latex which has been subjected to the protein decomposition treatment was subjected to the dilution treatment, the centrifugation treatment and the  
20 redispersion treatment to obtain a low ~~allergie~~ allergenic natural rubber latex which has been subjected to a protein decomposition treatment and a protein removing treatment.

Furthermore, the cream component was dried to obtain a low ~~allergie~~ allergenic natural rubber latex which has been  
25 subjected to a protein decomposition treatment and a protein

removing treatment.

Example 18

(Only protein decomposition treatment)

In the same manner as in Example 14 (namely, the HA  
5 latex is used as a starting material), except that  
aforementioned "Peptidase R" was used as the protease having  
an exopeptidase activity in place of aforementioned  
"Umamizyme" and that the amount was changed to 0.1 parts by  
weight based on 100 parts by weight of the rubber content of  
10 the latex, the decomposition treatment of the protein was  
carried out to obtain a low ~~allergie~~ allergenic natural  
rubber latex.

Furthermore, the rubber component of the low ~~allergie~~  
allergenic natural rubber latex thus obtained was coagulated  
15 and dried to obtain a low ~~allergie~~ allergenic natural rubber  
latex which has been subjected to a protein decomposition  
treatment.

(Protein decomposition treatment and protein removing  
treatment)

20 In the same manner as in Example 14, the low ~~allergie~~  
allergenic natural rubber latex which has been subjected to  
the protein decomposition treatment by the protease  
"Peptidase R" was subjected to the dilution treatment, the  
centrifugation treatment and the redispersion treatment to  
25 obtain a low ~~allergie~~ allergenic natural rubber latex which

has been subjected to a protein decomposition treatment and a protein removing treatment.

Furthermore, the cream component was dried to obtain a low ~~allergie~~ allergenic natural rubber latex which has been  
5 subjected to a protein decomposition treatment and a protein removing treatment.

#### Comparative Example 3

(Only protein decomposition treatment)

To 100 parts by weight of a rubber content of a field  
10 latex, 0.1 parts by weight of an alkali protease, 1.0 parts by weight of a nonionic surfactant and 0.12% of sodium naphthenate were added, thereby to stabilize the latex.

As the alkali protease, a protease, which is derived from bacteria and is also produced by microorganisms which  
15 belong to *Bacillus licheniformis* [manufactured by Novo-Nordisk Bioindustri A/S under the trade name of "Alcalase 2.0M"], was used. This alkali protease had a potency of 2.0 AU/g (pH 8.3) and has an optimum pH in an alkali range, as shown in Table 1, and also has an endopeptidase but has no  
20 exopeptidase activity.

After adjusting the pH to 9.2 by using sodium dihydrogenphosphate, the latex was aged by allowing to stand at 30°C for 24 hours to obtain a natural rubber latex which has been subjected to a protein decomposition treatment.

25 (Protein decomposition treatment and protein removing

treatment)

The low allergie allergenic natural rubber latex which has been subjected to the protein decomposition treatment was diluted with an aqueous 1% solution of a nonionic surfactant, 5 thereby to reduce the rubber content of the latex to 10%, and then subjected to a centrifugation treatment at 13000 rpm for 30 minutes. The cream component thus separated in the upper layer was taken out and then dispersed again in the same amount of water to obtain a natural rubber latex which has 10 been subjected to a protein decomposition treatment and a protein removing treatment.

Furthermore, the cream component was dried to obtain a deproteinized natural rubber latex.

[Evaluation of protein decomposition treatment]

15 The results of the evaluation of the protein decomposition treatment (the measurement of the nitrogen content and the measurement of the content index of the allergie allergenic protein) in Examples 13 to 18 and Comparative Example 3 are the same as those in Examples 1 to 20 6 and Comparative Example 1.

(Analysis of molecular weight of protein)

The results of the analysis of the molecular weight of the protein with respect to the natural rubber latexes obtained in Example 13 and Comparative Example 3 are the same 25 as those in Example 1 (Fig. 1) and Comparative Example 1



(Fig. 3).

[Preparation of ~~deprotenized~~ deproteized natural rubber]

#### Example 19

5 (Decomposition of protein by alkali protease)

To 100 parts by weight of a rubber content of a field latex, 1.0 parts by weight of a nonionic surfactant and 0.12% of sodium naphthenate were added, thereby to stabilize the latex. To 100 parts by weight of the rubber content of this  
10 latex, 0.1 parts by weight of an alkali protease was added, and then the latex was aged by allowing to stand at 30°C for 24 hours.

As the alkali protease, a protease, which is a protease derived from bacteria and is produced by microorganisms which  
15 belong to *Bacillus licheniformis* as a kind of bacteria of the genus *Bacillus* [manufactured by Novo-Nordisk Bioindustri A/S under the trade name of "Alcalase 2.0M"], was used. This alkali protease had a potency of 2.0 AU/g (pH 8.3) and has an optimum pH in an alkali range, as shown in Table 1, and also  
20 has an endopeptidase but has no exopeptidase activity.

(Decomposition of protein by protease having exopeptidase activity)

To the aged latex, an aqueous 5% sodium dihydrogenphosphate solution was added, thereby to adjust the  
25 pH to 7.0. To 100 parts by weight of the rubber content of

the latex, 0.1 parts by weight of a protease having an exopeptidase activity was added. After the addition of the protease, the latex was aged again by allowing to stand at 30°C for 24 hours.

5       As the protease, a protease, which has both an exopeptidase activity and an endopeptidase activity and an optimum pH in a neutral range, and is also produced by microorganisms which belong to *Aspergillus oryzae* [manufactured by Amano Enzyme, Inc. under the trade name of  
10 "Umamizyme"], was used (see Table 2). This protease had a peptidase activity of 70 u/g or more (pH 7.0, LGG (L-Leucyl-Glycyl-Glycine) method).

(Removal of protein and decomposition product thereof)

After the completion of the enzyme treatment, the latex  
15 was diluted with an aqueous 1% solution of a nonionic surfactant, thereby to reduce the rubber content of the latex to 10%, and then subjected to a centrifugation treatment at 13000 rpm for 30 minutes. The cream component thus separated in the upper layer was diluted again and then subjected to  
20 the second centrifugation treatment in the same manner as described above.

The resulting cream component was dispersed again in water to obtain a deproteinized natural rubber latex. The deproteinized natural rubber latex was coagulated and dried  
25 to obtain a deproteinized natural rubber.

## Example 20

(Decomposition of protein by alkali protease)

A high ammonia latex (hereinafter referred to as a "HA latex") was diluted so that so that the rubber content is  
5 reduced to 30% by weight. To 100 parts by weight of a rubber content of a field latex, 1.0 parts by weight of a nonionic surfactant and 0.12% of sodium naphthenate were added, thereby to stabilize the latex. To 100 parts by weight of the rubber content of this latex, 0.1 parts by weight of an  
10 alkali protease (aforementioned "Alcalase 2.0M") was added, and then the latex was aged by allowing to stand at 30°C for 24 hours.

(Decomposition of protein by protease having exopeptidase activity)

15 To the aged latex, an aqueous 5% sodium dihydrogenphosphate solution was added, thereby to adjust the pH to 7.0. To 100 parts by weight of the rubber content of the latex, 0.1 parts by weight of a protease having an exopeptidase activity (aforementioned "Umamizyme") was added.  
20 After the addition of the protease, the latex was aged again by allowing to stand at 30°C for 24 hours.

(Removal of protein and decomposition product thereof)

After the completion of the enzyme treatment, the latex was diluted with an aqueous 1% solution of a nonionic  
25 surfactant, thereby to reduce the rubber content of the latex

to 10%, and then subjected to a centrifugation treatment at 13000 rpm for 30 minutes.

The cream component thus separated in the upper layer was diluted again and then subjected to the second  
5 centrifugation treatment in the same manner as described above.

The resulting cream component was dispersed again in water to obtain a deproteinized natural rubber latex. The deproteinized natural rubber latex was coagulated and dried  
10 to obtain a deproteinized natural rubber.

#### Example 21

(Decomposition of protein by alkali protease)

In the same manner as in case of the "decomposition of the protein by the alkali protease" of Example 19, the  
15 protein in the field latex was decomposed by the alkali protease (aforementioned "Alcalase 2.0M").

(Decomposition of protein by protease having exopeptidase activity)

In the same manner as in case of the "decomposition of  
20 the protein by the protease having an exopeptidase activity" of Example 19, except that a protease produced by microorganisms which belong to *Aspergillus mellus* [manufactured by Amano Enzyme, Inc. under the trade name of P "Amano" 3G] was used as the protease having an exopeptidase  
25 activity in place of aforementioned "Umamizyme" and that the

amount was changed to 0.1 parts by weight based on 100 parts by weight of the rubber content of the latex, the decomposition treatment of the protein was carried out.

The protease P "Amano" 3G is a protease, which has a  
5 protein digestion potency of 10000 u/g or more (pH 7.0, Amano method) and has both an exopeptidase activity and an endopeptidase activity and also has an optimum pH in a neutral range as shown in Table 2.

(Removal of protein and decomposition product thereof)

10 In the same manner as in case of the "removal of the protein and the decomposition product thereof" of Example 19, except that the latex was used after the completion of the enzyme treatment by the protease P "Amano" 3G, the centrifugation treatment was carried out to obtain a  
15 deproteinized natural rubber latex and a deproteinized natural rubber.

#### Example 22

(Decomposition of protein by alkali protease)

20 In the same manner as in case of the "decomposition of the protein by the alkali protease" of Example 20, the protein in the HA latex was decomposed by the alkali protease (aforementioned "Alcalase 2.0M").

(Decomposition of protein by protease having exopeptidase activity)

25 In the same manner as in case of the "decomposition of

the protein by the protease having an exopeptidase activity" of Example 20, except that aforementioned P "Amano" 3G was used as the protease having an exopeptidase activity in place of aforementioned "Umamizyme" and that the amount was changed  
5 to 0.1 parts by weight based on 100 parts by weight of the rubber content of the latex, the decomposition treatment of the protein was carried out.

(Removal of protein and decomposition product thereof)

In the same manner as in case of the "removal of the  
10 protein and the decomposition product thereof" of Example 20, except that the latex was used after the completion of the enzyme treatment by the protease P "Amano" 3G, the centrifugation treatment was carried out to obtain a deproteinized natural rubber latex and a deproteinized  
15 natural rubber.

#### Example 23

(Decomposition of protein by alkali protease)

In the same manner as in case of the "decomposition of the protein by the alkali protease" of Example 19, the  
20 protein in the field latex was decomposed by the alkali protease (aforementioned "Alcalase 2.0M").

(Decomposition of protein by protease having exopeptidase activity)

In the same manner as in case of the "decomposition of  
25 the protein by the protease having an exopeptidase activity"

of Example 19, except that a protease produced by microorganisms which belong to *Rhizopus oryzae* [manufactured by Amano Enzyme, Inc. under the trade name of "Peptidase R"] was used as the protease having an exopeptidase activity in place of aforementioned "Umamizyme" and that the amount was changed to 0.1 parts by weight based on 100 parts by weight of the rubber content of the latex, the decomposition treatment of the protein was carried out.

The protease "Peptidase R" is a protease, which has a peptidase activity of 420 u/g or more (pH 7.0, LGG method) and has both an exopeptidase activity and an endopeptidase activity and also has an optimum pH in a neutral range as shown in Table 2.

(Removal of protein and decomposition product thereof)

In the same manner as in case of the "removal of the protein and the decomposition product thereof" of Example 19, except that the latex was used after the completion of the enzyme treatment by the protease "Peptidase R", the centrifugation treatment was carried out to obtain a deproteinized natural rubber latex and a deproteinized natural rubber.

#### Example 24

(Decomposition of protein by alkali protease)

In the same manner as in case of the "decomposition of the protein by the alkali protease" of Example 20, the

protein in the field latex was decomposed by the alkali protease (aforementioned "Alcalase 2.0M").

(Decomposition of protein by protease having exopeptidase activity)

5        In the same manner as in case of the "decomposition of the protein by the protease having an exopeptidase activity" of Example 20, except that aforementioned "Peptidase R" was used as the protease having an exopeptidase activity in place of aforementioned "Umamizyme" and that the amount was changed  
10 to 0.1 parts by weight based on 100 parts by weight of the rubber content of the latex, the decomposition treatment of the protein was carried out.

(Removal of protein and decomposition product thereof)

15        In the same manner as in case of the "removal of the protein and the decomposition product thereof" of Example 20, except that the latex was used after the completion of the enzyme treatment by the protease "Peptidase R", the centrifugation treatment was carried out to obtain a deproteinized natural rubber latex and a deproteinized  
20 natural rubber.

#### Comparative Example 4

A deproteinized natural rubber was prepared according to the method described in Japanese Patent No. 2,905,005.

A HA latex was diluted so that the rubber content is  
25 reduced to 30% by weight. To 100 parts by weight of a rubber



content of a field latex, 0.1 parts by weight of an alkali protease, 1.0 parts by weight of a nonionic surfactant and 0.12% of sodium naphthenate were added, thereby to stabilize the latex.

5       As the alkali protease, a protease, which is a protease derived from bacteria and is produced by microorganisms which belong to *Bacillus licheniformis* as a kind of bacteria of the genus *Bacillus* [manufactured by Novo-Nordisk Bioindustri A/S under the trade name of "Alcalase 2.0M"], was used. This  
10 alkali protease had a potency of 2.0 AU/g (pH 8.3) and has an optimum pH in an alkali range, as shown in Table 1, and also has an endopeptidase but has no exopeptidase activity.

After adjusting the pH to 9.2 by using sodium dihydrogenphosphate, the latex was aged by allowing to stand  
15 at 30°C for 24 hours.

After the completion of the enzyme treatment, the latex was diluted with an aqueous 1% solution of a nonionic surfactant, thereby to reduce the rubber content of the latex to 10%, and then subjected to a centrifugation treatment at  
20 13000 rpm for 30 minutes.

The cream component thus separated in the upper layer was dispersed again in water to obtain a deproteinized natural rubber latex. The cream component was coagulated and dried to obtain a deproteinized natural rubber.

25       [Evaluation of protein decomposition treatment]

The results of the evaluation of the protein decomposition treatment (the measurement of the nitrogen content and the measurement of the content index of the ~~allergic~~ allergenic protein) in Examples 19 to 24 and Comparative Example 4 are the same as those in Examples 7 to 12 and Comparative Example 2 shown in Table 4.

(Measurement of infrared absorption spectrum)

A crude rubber film for measuring an infrared absorption spectrum was obtained by taking out each (36 g) of the deproteinized natural rubber latexes obtained in Example 19 and Comparative Example 4, spreading over the latex on a glass plate of 18 cm × 12 cm in size, dried by allowing to stand at room temperature, peeling off from the glass plate, drying the surface contacted with the glass surface for a day, and drying under vacuum.

The film was placed on a KBr plate and the absorbance was measured by a Fourier infrared spectrometer JASCO 5300.

As a result, an absorption at  $3280\text{ cm}^{-1}$  of polypeptide could not detected with respect to any samples made from the latexes of Example 19 and Comparative Example 4.

(Analysis of molecular weight of protein)

The results of the analysis of the number-average molecular weight  $\langle M_n \rangle$  of the remained protein and the protein decomposition product with respect to the latexes of Example 19, 20, 21 and 22 and Comparative Example 4 are the same as

those shown in Figs. 5, 6, 7, 8 and 9.